ORPI Cycle 6

Final Report

Road Inventory and Condition Assessment of Paved Routes Organ Pipe Cactus National Monument







Federal Lands Highway
Road Inventory Program

Prepared By:

Federal Highway Administration Eastern Federal Lands Highway Division Road Inventory Program (RIP)

Report Date: July 2017

Organ Pipe Cactus National Monument in Arizona




Table of Contents

SEC	TION	PAGE NO
1.	INTRODUCTION	1-1
2.	PARK ROUTE INVENTORY	
	Route ID Report, Subcomponent Report, and Changes Report (As Applicable)	2 - 1
3.	PARK SUMMARY INFORMATION	
	Parkwide Paved Route Condition Summary	3 - 1
	Explanation of Condition Descriptions	3 - 2
	Route-Level Condition Summary Reports for Data Collection Vehicle, Manually Rated, and Parking Area Routes (As Applicable)	3 - 3
4.	PARK ROUTE LOCATION MAPS	
	Route Location Key Map	4 - 1
	Route Location Area Map(s)	4 - 2
	Route Condition Key Map – PCR Mile by Mile	4 - 5 4 - 6
	Route Condition Area Map(s) – PCR Mile by Mile	4 - 0
5.	PAVED ROAD CONDITION RATING SHEETS	
	Paved Road Pages	5 - 1
6.	PAVED PARKING AREA CONDITION RATING SHEETS	
	Paved Parking Area Pages	6 - 1
7.	ROAD MILEPOST INFORMATION	
	Road Milepost Information and Logs	7 - 1
8.	APPENDIX	
	Improvements to the RIP Index Equations and Determination of PCR	8 - 1
	Description of the Rating System	8 - 2
	Explanation of the Condition Descriptions	8 - 3
	Description of Pavement Treatment Types	8 - 4
	Appendix A: Methodology for Determining Condition Ratings with the Data Collection Vehicle (DCV)	8 - 5
	Appendix B: Methodology for Determining Condition Ratings Using Manual Rating Procedures	8 - 20
	Appendix C: Description of Cycle 6 Deliverables	8 - 29
	Appendix D: Glossary of Terms and Abbreviations	8 - 33

Section 1 Introduction





Introduction

The Federal Highway Administration's (FHWA), Road Inventory Program (RIP) inventories all roads and parking areas in the National Park System, and performs condition inspections on all paved roads and parking areas for the National Park Service (NPS). This report contains the results of the Cycle 6 condition assessment of paved roads and parking lots for this park unit. This assessment was done using an automated, state-of-the-art pavement inspection vehicle as well as manual ratings. This information represents the condition of the paved assets at the time of the inspection. The pavement management system utilized by FHWA and the NPS uses these assessments to estimate future conditions and help prioritize pavement maintenance and rehabilitation projects. Further information about RIP data and its role in managing paved roads and bridges can be obtained by contacting the NPS Regional Transportation Program Manager.

A History of the Road Inventory Program:

The FHWA, in the mid-1970s, was charged with the task of identifying surface condition deficiencies and corrective priorities on NPS roads and parkways. Additionally, FHWA was tasked with establishing an integrated maintenance features inventory, locating features such as culverts, guardrails, and signs, among others, along NPS roads and parkways. As a result, in 1976 the NPS and FHWA entered into a Memorandum of Agreement (MOA) which established the RIP. This MOA was revised in 1980 to update RIP data collection standards and develop a long-range program to improve and maintain NPS roads to designated condition standards and establish a pavement management program.

The FHWA completed the initial phase of inventory in the early 1980s. As a result of this effort, each NPS unit included in the collection received a RIP Report known as the "Brown Book" which contained information that was inventoried during this first RIP phase. In the 1990s, a cyclical program was developed, and since then five cycles of collection have been completed. Cycle 6 is currently in progress. A summary of the RIP collection cycles is shown in the table below.

Cycle	Years	Parks Collected
Cycle 1	1994 - 1997	° 44 Large Parks
Cycle 2	1997 - 2001	79 Large Parks5 Small Parks
Cycle 3	2001 - 2004	All Large ParksAll Small Parks
Cycle 4	2006 - 2010	86 Large ParksSeveral Small Parks
Cycle 5	2010 - 2014	 All Large Parks (Only functional class 1, 2, 7, and new/modified routes collected) All Small Parks (all roads and parking areas collected)
Cycle 6	2014 – 2020 (±)	 All roads and parking areas collected at all Parks Additional partial collections of functional class 1, 2, and 7 roads at Large Parks Cycle 6 is expected to last 6 years

Note: Large Parks have ≥ 10 Paved Miles; Small Parks have < 10 Paved Miles

Since 1984, the Road Inventory Program has been funded through the Federal Lands Highway Park Roads and Parkways (PRP) Program. Currently, coordination of the RIP with Federal Lands Highway (FLH) is under the NPS Washington Headquarters Park Facility Management Division. The FLH Washington office coordinates policy and prepares national reports and needs assessment studies for Congress.

In 1998, the Transportation Equity Act for the 21st Century (TEA-21) amended Title 23 U.S.C., and inserted Section 204(a)(6) requiring the FHWA and NPS, to develop by rule, a Pavement Management System (PMS) applied to park roads and parkways serving the National Park System.

In 2012, the Moving Ahead for Progress in the 21st Century Act (MAP-21) amended Title 23 U.S.C., and under Section 203(c)(1-2) stated that the National Park Service in cooperation with the DOT/FHWA, shall maintain a comprehensive national inventory of their transportation facilities, with the goal of quantifying transportation infrastructure needs within the National Park System.

A History of the Pavement Management System:

In 2005, the FHWA began implementing the use of a pavement management system to assist the NPS in prioritizing Pavement Maintenance and Rehabilitation activities. The system used by FHWA is the Highway Pavement Management Application (HPMA), which has the ability to store inventory and condition data from RIP and forecast future performance using prediction models. Outputs include performance and condition reports at the National, Regional, Park, or Route level. Regional prioritized lists and optimizations have been produced for most regions, and the Service's overall roadway Deferred Maintenance is calculated via the HPMA.

Overview of Cycle 6:

Cycle 6 launched in the spring of 2014 and will again comprise all NPS park units that are served by paved roads and/or parking areas. For Cycle 6, all paved roads (approximately 5,700 miles) and parking areas will be collected in all parks at least once, while the primary routes (functional class 1, 2, and 7 roads) at Large Parks will have additional collections. These multiple collections will provide updated condition data on a majority of the NPS's primary road network and help build a better pavement management system, allowing for more accurate pavement performance prediction models.

FLH is responsible for the accuracy of all data presented in this report. Any questions or comments concerning the contents of this report should be directed to the national RIP Coordinator located in Sterling, Virginia.

Respectfully,

FHWA RIP Team

FHWA/Eastern Federal Lands 21400 Ridgetop Circle Sterling, VA 20166 (571) 434-1574 FHWA/Central Federal Lands 12300 West Dakota Ave Lakewood, CO 80228 (720) 963-3556

Section 2 Park Route Inventory





Page 1 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle
MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas NC = Not Collected

ORPI

				Ę		ROAD INVENTORY (1100 SERIES FMSS	LOCATION	S)				<u> </u>			
Route No.	Cycle Collected	lteration Collected	FMSS Number	Concessio	Route Name	Route Des	cription To	Maintenance District	댎	Paved Miles	Unpaved Miles	Total Mileage	Function Class	Area (SQ FT)	Surf. Type	Area Map
0010	6	1	72387		VISITOR CENTER DRIVE	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 17.42 ON RIGHT	TO ROUTE 0100 (RESIDENCE ACCESS ROAD) AT MP 0.02 ON RIGHT		YES	0.34	0.00	0.34	1		AS	1A
0011	6	1	74168		AJO MOUNTAIN DRIVE	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 17.42 ON LEFT	TO END OF LOOP		YES	3.18	14.87	18.05	1		AS	1,1A
0012	6	1	74253		PUERTO BLANCO DRIVE	FROM ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.32 ON RIGHT	TO ROUTE 5000 (STATE HIGHWAY 85) AT MP 21.70 ON RIGHT		YES	1.68	35.58	37.26	1		AS	1,1A
0100	6	1	72452		RESIDENCE ACCESS ROAD	FROM ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.31 ON LEFT	TO END OF LOOP		NO	1.14	0.00	1.14	6		AS	1A
0101	6	1	72864		TWIN PEAKS ACCESS ROAD	FROM ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.17 ON LEFT	TO BEGINING OF ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD) AND END OF ROUTE 0200 (CAMPGROUND LOOP ROAD)		YES	1.32	0.00	1.32	2		AS	1A,1B
0200	6	1	72866		CAMPGROUND LOOP ROAD	FROM ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD) ON LEFT	TO END OF ROUTE 0101 (TWIN PEAKS ACCESS ROAD) AND BEGIN OF ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)		YES	0.82	0.00	0.82	3		AS	1B
0201	NC		74164		CAMINO DE DOS REPUBLICAS	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 21.91 ON LEFT	TO DOS LOMITAS RANCH		YES	0.00	4.90	4.90	2		NV	
0202	NC		74266		SENITA BASIN ROAD	FROM ROUTE 0012 (PUERTO BLANCO DRIVE)	TO ROUTE 0901 (SENITA BASIN PARKING)		YES	0.00	4.44	4.44	2		NV	
0203	NC		74269		QUITOBAQUITO ROAD	FROM ROUTE 0012 (PUERTO BLANCO DRIVE)	TO ROUTE 0900 (QUITOBAQUITO PARKING)		YES	0.00	0.40	0.40	2		NV	

Page 2 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line MRP = Manually Rated Polygon

PKG = Parking Areas NC = Not Collected

ORPI

ROAD INVENTORY (1100 SERIES FMSS LOCATIONS)																
Route No.	Cycle Collected	lteration Collected	FMSS Number	Concessio	Route Name	Route Desc	cription To	Maintenance District	FLT	Paved Miles	Unpaved Miles	Total Mileage		Area (SQ FT)	Surf. Type	Area Map
0204	NC		74171		ALAMO CANYON ROAD	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 7.63 ON LEFT	TO ALAMO CANYON TRAILHEAD		YES	0.00	3.30	3.30	2		NV	
0205	6	1	72685		MAINTENANCE ACCESS ROAD	FROM ROUTE 0100 (RESIDENCE ACCESS ROAD) AT MP 0.07 ON LEFT	TO ROUTE 0903 (MAINTENANCE YARD)		YES	0.08	0.00	0.08	5		AS	1A
0206	6	1	102406		CAMPGROUND SITES 1-6 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.01 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.76 ON LEFT		YES	0.09	0.00	0.09	3		AS	1 B
0207	6	1	102418		CAMPGROUND SITES 7-15 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.04 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.75 ON LEFT		YES	0.12	0.00	0.12	3		AS	1 B
0208	6	1	102419		CAMPGROUND SITES 16-23 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.05 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.73 ON LEFT		YES	0.13	0.00	0.13	3		AS	1 B
0209	6	1	102421		CAMPGROUND SITES 24-34 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.07 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.72 ON LEFT		YES	0.15	0.00	0.15	3		AS	1 B
0210	6	1	102422		CAMPGROUND SITES 35-45 ACCESS	(CAMPGROUND LOOP ROAD) AT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.70 ON LEFT		YES	0.16	0.00	0.16	3		AS	1 B
0211	6	1	102424		CAMPGROUND SITES 46-57 ACCESS	, , , , , , , , , , , , , , , , , , , ,	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.69 ON LEFT		YES	0.17	0.00	0.17	3		AS	1 B
0212	6	1	102425		CAMPGROUND SITES 58-70 ACCESS	1;	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.67 ON LEFT		YES	0.18	0.00	0.18	3		AS	1 B
0213	6	1	102426		CAMPGROUND SITES 71-85 ACCESS	1;	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.66 ON LEFT		YES	0.19	0.00	0.19	3		AS	1 B

Page 3 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas
NC = Not Collected

ORPI

ROAD INVENTORY (1100 SERIES FMSS LOCATIONS)																
Route No.	Cycle Collected	Iteration Collected	FMSS Number	Concessio	Route Name	Route Desc	cription To	Maintenance District	FLTP	Paved Miles	Unpaved Miles	Total Mileage		Area (SQ FT)	Surf. Type	Area Map
0214	6	1	102427		CAMPGROUND SITES 86-95 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.15 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.64 ON LEFT		YES	0.20	0.00	0.20	3		AS	1 B
0215	6	1	102428		CAMPGROUND SITES 96-112 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.16 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.63 ON LEFT		YES	0.21	0.00	0.21	3		AS	1 B
0216	6	1	102429		CAMPGROUND SITES 113-128 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.18 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.62 ON LEFT		YES	0.21	0.00	0.21	3		AS	1B
021 <i>7</i>	6	1	102430		CAMPGROUND SITES 129-145 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.20 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.60 ON LEFT		YES	0.22	0.00	0.22	3		AS	1 B
0218	6	1	102431		CAMPGROUND SITES 146-158 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.21 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.59 ON LEFT		YES	0.23	0.00	0.23	3		AS	1 B
0219	6	1	102432		CAMPGROUND SITES 159-174 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.23 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.58 ON LEFT		YES	0.23	0.00	0.23	3		AS	1B
0220	6	1	102435		CAMPGROUND SITES 175-191 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.24 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.57 ON LEFT		YES	0.25	0.00	0.25	3		AS	1 B
0221	6	1	102434		CAMPGROUND SITES 192-208 ACCESS	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.25 ON LEFT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.54 ON LEFT		YES	0.25	0.00	0.25	3		AS	1 B
0222	NC		72867		50 K WATER TANK ROAD	FROM ROUTE 0906 (GROUP CAMPGROUND PARKING)	to 50k water tank		NO	0.00	0.19	0.19	6		NV	
0401	6	1	72473		SPUR RESIDENCE ROAD WEST	FROM ROUTE 0402 (SPUR RESIDENCE ROAD EAST) AT MP 0.02 ON LEFT	TO ROUTE 0912 (HOUSING AREA DUPLEX HOUSING PARKING)		NO	0.07	0.00	0.07	6		AS	1A

Page 4 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas
NC = Not Collected

ORPI

ROAD INVENTORY (1100 SERIES FMSS LOCATIONS)																
Route No.	ycle	Iteration Collected	FMSS Number	ncessic	Route Name	Route Des	<u> </u>	Maintenance District	FLTP	Paved	Unpaved Miles	Total	unction	Area (SQ FT)	Surf. Type	Area Map
NO.	ΰΰ	≗ິບ	Number	8		From	То	District			-	Mileage	ᅹᆼ	(3Q FI)	ı ype	Map
0402	6	1	72455		SPUR RESIDENCE ROAD EAST	FROM ROUTE 0100 (RESIDENCE ACCESS ROAD) AT MP 0.53 ON RIGHT	TO END OF UNPAVED LOOP		NO	0.09	0.03	0.12	6		AS	1A
0403	6	1	102994		CAMPGROUND HOUSING ROAD	FROM ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD) AT MP 0.03 ON RIGHT	TO ROUTE 0909 (CAMPGROUND HOUSING PARKING)		NO	0.05	0.00	0.05	6		AS	1 B
0404	NC		74274		POZO NUEVO ROAD	FROM ROUTE 0012 (PUERTO BLANCO DRIVE)	TO ROUTE 0405 (BATES WELL ROAD)		Ю	0.00	13.95	13.95	4		NV	
0405	NC		74277		BATES WELL ROAD	FROM WEST PARK BOUNDARY	TO NORTH PARK BOUNDARY		YES	0.00	13.25	13.25	2		NV	
0406	NC		74280		ARMENTA ROAD	FROM ROUTE 0405 (BATES WELL ROAD)	TO ROUTE 5000 (STATE HIGHWAY 85)		NO	0.00	9.35	9.35	3		NV	
0407	NC		72874		SEWAGE LAGOON ROAD	FROM ROUTE 0908 (DUMP STATION LOOP)	TO SEWAGE LAGOON		NO	0.00	0.25	0.25	6		NV	
0408	6	1	72482		100 K WATER TANK ROAD	FROM ROUTE 0100 (RESIDENCE ACCESS ROAD) AT MP 0.84 ON RIGHT	TO WATER TANK		NO	0.10	0.20	0.29	6		AS	1A
0409	6	1	72870		GROUP CAMPGROUND ACCESS ROAD	FROM END OF ROUTE 0101 (TWIN PEAKS ACCESS ROAD)	TO ROUTE 0906 (GROUP CAMPGROUND PARKING)		YES	0.14	0.00	0.14	3		AS	1 B
0410	NC		72862		DOMESTIC WATER WELLS ROAD	FROM ROUTE 0101 (TWIN PEAKS ACCESS ROAD) AT MP 0.23 ON LEFT	TO WATER WELLS		NO	0.00	0.23	0.23	6		NV	
0412	NC		74286		TIGER CAGE ROAD	FROM ROUTE 0012 (PUERTO BLANCO DRIVE)	TO BORROW PIT		NO	0.00	0.50	0.50	6		NV	
0413	NC		102995		FIREARMS RANGE ROAD	FROM STATE ROUTE 85	TO FIREARMS RANGE		NO	0.00	0.50	0.50	6		NV	
0416	NC		72485		VIP ROAD	FROM ROUTE 0100 (RESIDENCE ACCESS ROAD) AT MP 1.08 ON LEFT	TO END		NO	0.00	0.10	0.10	6		GR	
0417	NC		92462		MAINTENANCE BONEYARD ROAD	FROM ROUTE 0205 (MAINTENANCE ACCESS ROAD)	TO END		NO	0.00	0.10	0.10	6		NV	

Page 5 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line MRP = Manually Rated Polygon

PKG = Parking Areas

NC = Not Collected

ORPI

	ROAD INVENTORY (1100 SERIES FMSS LOCATIONS)														
Route No.	Cycle Collected Iteration Collected	FMSS Number	Concessio	Route Name	Route Des	cription To	Maintenance District	FLTP	Paved Miles	Unpaved Miles	Total Mileage	Function Class	Area (SQ FT)	Surf. Type	Area Map
0418	NC	230320		TOWER SITE 170 ROAD	FROM ROUTE 0406 (ARMENTA ROAD)	TO END		NO	0.00	6.00	6.00	6		NV	
0419	NC	234263		TOWER SITE 310 ROAD	FROM BORDER ROAD EAST SIDE OF LOOPVILLE	TO 1.25 MI FROM STATE PROPERTY		NO	0.00	1.25	1.25	6		NV	

	NON-NPS ROADS INVENTORY														
Route No.	Cycle Collected Iteration Collected	FMSS Number	Concession	Route Name	Route Des	cription To	Maintenance District	FLTP	Paved Miles	Unpaved Miles	Total t	Class	Area (SQ FT)	Surf. Type	Area Map
5000	5 1			STATE HIGHWAY 85	FROM NORTH PARK BOUNDARY	TO SOUTH PARK BOUNDARY		NO	22.56	0.00	22.56			AS	1,1A

	PARKING AREA INVENTORY (1300 SERIES FMSS LOCATIONS)												
Route	le ected	lteration Collected	FMSS	cession				Maintenance	FLTP	Access	Area	Surf.	Area
No.	Cycle	5 S	Number	ŝ	Route Name	From	То	District	균	Level	(SQ FT)	Туре	Мар
0900	NC		102998		QUITOBAQUITO PARKING	FROM ROUTE 0203 (QUITOBAQUITO ROAD)	TO PARKING		NO	PUBLIC	7,200	NV	
0901	NC		103000		SENITA BASIN PARKING	FROM END OF ROUTE 0202 (SENITA BASIN ROAD)	TO PARKING		80	PUBLIC	5,700	NV	
0902	NC		102992		GOLDEN BELL MINE PARKING	FROM ROUTE 0012 (PUERTO BLANCO DRIVE)	TO PARKING		NO	PUBLIC	5,100	NV	
0903	6	1	72690		MAINTENANCE YARD	FROM ROUTE 0205 (MAINTENANCE ACCESS ROAD)	TO PARKING		NO	NONPUBLIC	33,594	AS	1A
0904A	6	1	72424		VISITOR CENTER PARKING A	FROM ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.07 ON RIGHT	TO ROUTE 0905 (OFFICE PARKING)		YES	PUBLIC	36,266	AS	1A

Page 6 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas
NC = Not Collected

ORPI

PARKING AREA INVENTORY (1300 SERIES FMSS LOCATIONS)													
Route	Cycle Collected	rtion ected	FMSS	cession		Route De	scription	Maintenance	₽.	Access	Area	Surf.	Area
No.	ζ̈ς	S E	Number	ទឹ	Route Name	From	То	District	FF	Level	(SQ FT)	Туре	Мар
0904В	6	1	105672		VISITOR CENTER PARKING B	ADJACENT TO ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.1 ON LEFT			YES	PUBLIC	8,145	AS	1A
0905	6	1	102991		OFFICE PARKING	FROM ROUTE 0904A (VISITOR CENTER PARKING A)	TO PARKING		NO	NONPUBLIC	7,277	AS	1A
0906	6	1	10298 <i>7</i>		GROUP CAMPGROUND PARKING	FROM END OF ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)	TO PARKING		YES	PUBLIC	12,611	AS	1B
0907	6	1	102774		CAMPGROUND PARKING	ADJACENT TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.22 ON RIGHT			YES	PUBLIC	995	AS	1 B
0908	6	1	102436		DUMP STATION LOOP	FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.34 ON RIGHT	TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.39 ON RIGHT		YES	PUBLIC	<i>7,</i> 621	AS	1B
0909	6	1	102773		CAMPGROUND HOUSING PARKING	FROM END OF ROUTE 0403 (CAMPGROUND HOUSING ROAD)	TO PARKING		NO	NONPUBLIC	2,638	AS	1B
0910	6	1	109708		TILLOTSON PEAK WAYSIDE PARKING	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 14.67 ON LEFT	TO PARKING		YES	PUBLIC	28,505	AS	- 1
0911	6	1	109712		AJO MOUNTAINS WAYSIDE PARKING	FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 4.89 ON RIGHT	TO PARKING		YES	PUBLIC	30,415	AS	- 1
0912	6	1	115987		HOUSING AREA DUPLEX HOUSING PARKING	FROM END OF ROUTE 0401 (SPUR RESIDENCE ROAD WEST)	TO PARKING		NO	NONPUBLIC	1,747	AS	1A
0913	NC		237607		BATES WELL PARKING	FROM ROUTE 0405 (BATES WELL ROAD)	TO PARKING		Ю	PUBLIC	1 <i>5</i> ,000	NV	
0914	NC		235017		HORSE TRAILER PULLOUT	FROM ROUTE 5000 (STATE HIGHWAY 85) (AT MILEPOST 70)	TO ROUTE 5000 (STATE HIGHWAY 85)		NO	PUBLIC	235,017	GR	
0915	NC				RESOURCE / LAW ENFORCEMENT PARKING	FROM ROUTE 0205 (MAINTENANCE ACCESS ROAD)	TO PARKING		NO	NONPUBLIC		GR	

Page 7 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

 $\mathsf{DCV} = \mathsf{Data} \ \mathsf{Collection} \ \mathsf{Vehicle}$

MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas

NC = Not Collected

Cycle 6 Summary Totals for Organ Pipe Cactus National Monument

Cycle 6 Route Totals

	NPS Maintained	Concessionaire Maintained	Park Totals
Paved Roads, Data Collection Vehicle Rated (Miles)	7.03	0	7.03
Paved Roads, Manually Rated Length (Miles)	4.95	0	4.95
Paved Roads, Manually Rated Area (Sq. Ft.)	0	0	0
Unpaved Roads (Miles)	109.38	0	109.38
Paved Parking (Sq. Ft.)	169,814	0	169,814
Unpaved Parking (Sq. Ft.)	268,017	0	268,017

Cycle 6 Lane Miles and Overall Pavement Condition

	Lanes Miles*	Pavement Condition Rating**
Data Collection Vehicle Routes	10.60	87
Manually Rated Roads	7.45	79
Parking Areas	2.92	87

^{*} Equivalent Lane Miles are calculated by route using the following equations:

- DCV and MRLs = $(PAVE_WIDTH \times PAVED_MI) / 11$ foot lane

- MRPs and PKGs = $SQ_{FEET} / 5280 / 11$ foot lane

-Excellent = 97

-Good = 90

-Fair = 73

-Poor = 53, 30, or 0

-Construction / Not Rated = -1

^{**}Parking and Manually Rated Routes are assigned the following PCR values based on the type of observed distresses:

Page 8 of 8

Cycle 6 NPS / RIP Route ID Report

(Numerical By Summary Route and Subcomponent #)



Shading Color Key

Report Date: 07/27/2017

White = Paved Routes, DCV Driven

Grey = Paved Routes, DCV not Driven

Black = Non-NPS Routes

= Concession Route

Yellow = Unpaved Routes, DCV not Driven

Blue = Paved Parking Areas

Green = Unpaved Parking Areas

Red text denotes:

*Unpaved route data was obtained from the NPS and was not collected by the Road Inventory Program (RIP).

DCV = Data Collection Vehicle

MRL = Manually Rated Line

MRP = Manually Rated Polygon

PKG = Parking Areas
NC = Not Collected

General Park Road Functional Classification (FC) Table

FC	Туре	User Access	Description	Route Numbers
1	Principal Park Road Rural Parkway	Public	Roads which constitute the main access route, circulatory tour, or thoroughfare for park visitors. Rural Parkways (e.g. Natchez Trace) are numbered 0001 - 0009.	0001 - 0009 0010 - 0099
2	Connector Park Road	Public	Roads which provide access within a park to areas of scenic, scientific, recreational or cultural interest, such as overlooks, campgrounds, etc.	0100 - 0199
3	Special Purpose Park Road	Public	Roads which provide circulation within public areas, such as campgrounds, picnic areas, visitor center complexes, concessionaire facilities, etc. These roads generally serve low-speed traffic and are often designed for one-way circulation.	0200 - 0299
4	Primitive Park Road	Public	Roads which provide circulation through remote areas and/or access to primitive campgrounds and undeveloped areas. These roads frequently have no minimum design standards and their use may be limited to specially equipped vehicles. Note: Functional Classes 3 and 4 have the same route numbers because, historically, they were numbered similarly.	0200 - 0299
5	Administrative Park Road	Public	All public roads intended for access to administrative developments or structures such as park offices, employee quarters, or utility areas.	0400 - 0499
6	Administrative Park Road (Restricted Access)	Nonpublic	All roads normally closed to the public, including patrol roads, truck trails, and other similar roads. Note: Functional Classes 5 and 6 have the same route numbers because historically they were numbered similarly and often there is little distinction between these routes. For example, because utility areas and employee housing are often closed to the public, this restriction would result in classification of FC 6 rather than FC 5.	0400 - 0499
7	Urban Parkway	Public	These facilities serve high volumes of park and non-park related traffic and are restricted, limited-access facilities in an urban area. This category of roads primarily encompasses the major parkways which serve as gateways to our nation's capital. Other major park roads or portions thereof, however, may be included in this category.	0001 - 0009
8	City Street	Public	City streets are usually extensions of the adjoining street system that are owned and maintained by the National Park Service. The construction and/or reconstruction should conform with accepted local engineering practice and local conditions.	0600 - 0699
N/A	Non-NPS Roads	Public	State, County, or City owned roads which border, traverse, or provide access to Park Facilities or Locations. Non-NPS roads are not assigned functional classes and are driven for GPS and Video Log only.	5000 - 5999

Surface
Types

- AS Asphaltic Concrete Pavement
- BR Brick or Pavers Road Bed
- CB Cobble Stone Road Bed
- CO Portland Cement Concrete Pavement
- GR Gravel Road Bed
- NV Native or Dirt Material Road Bed
- OT Other Materials Road Bed

A park road system contains those roads within or giving access to a park or other unit of the NPS which are administered by the NPS, or by the Service in cooperation with other agencies. The assignment of a functional classification (FC) to a park road is not based on traffic volumes or design speed, but on the intended use or function of that road or route.

The historic route numbering system also included a 300 series for interpretive roads, and a 500 series for one-way roads. There are approximately 250 roads nationwide which are designated by the 300 and 500 series. The numbers for these roads will be maintained for reporting consistency. However, since these interpretive and one-way routes are not as clearly tied to a specific functional class, the 300 and 500 series will be discontinued for future use.

Route Identification Changes to Paved Routes from Previous Cycle Organ Pipe Cactus National Monument

	ROUTES MODIFIED FROM PREVIOUS INVENTORY:											
Route No.	Route Name	Type of Change	Comments									
0100	RESIDENCE ACCESS ROAD	FUNCTIONAL CLASS CHANGE	FUNCTIONAL CLASS CHANGED FROM 5 TO 6 BECAUSE THIS ROUTE IS AN ADMINISTRATIVE ROAD WITH RESTRICTED ACCESS.									
0401	SPUR RESIDENCE ROAD WEST	FUNCTIONAL CLASS CHANGE	FUNCTIONAL CLASS CHANGED FROM 5 TO 6 BECAUSE THIS ROUTE IS AN ADMINISTRATIVE ROAD WITH RESTRICTED ACCESS.									
0402	SPUR RESIDENCE ROAD EAST	FUNCTIONAL CLASS CHANGE	FUNCTIONAL CLASS CHANGED FROM 5 TO 6 BECAUSE THIS ROUTE IS AN ADMINISTRATIVE ROAD WITH RESTRICTED ACCESS.									
0903	MAINTENANCE YARD	SQ FEET CHANGE	GPS UPDATED TO ADD THE SECTION NEXT TO THE PARKING AREA IN CYCLE 6.									

Section 3 Park Summary Information





Parkwide Paved Route Condition Summary Organ Pipe Cactus National Monument

Table 1: Paved Route Miles and Parking Area Square Footages by Access Level and PCR


Breakdown of Pavement Condition Rating (PCR) Based on Access Level

	POOR	FAIR	GOOD	EXCELLENT	
	(PCR of 0 - 60)	(PCR of 61 - 84)	(PCR of 85 - 94)	(PCR of 95 -100)	
		PAVED	ROADS		
Functional Class	Length (miles)	Length (miles)	Length (miles)	Length (miles)	Total Mileage by FC
1	1.00	1.87	1.78	0.00	4.65
2	0.02	0.30	0.70	0.30	1.32
3	0.02	0.80	2.91	0.20	3.93
4					
5		0.02	0.06	0.00	0.08
6	0.14	0.26	0.62	0.40	1.42
7					
8					
Total Mileage by PCR	1.18	3.25	6.08	0.90	11.41
		PAVED P	ARKING		
Access Level	Area (sq. ft.)	Area (sq. ft.)	Area (sq. ft.)	Area (sq. ft.)	Total Area
PUBLIC	12,611		111,947		124,558
NONPUBLIC			45,256		45,256
Total Area by PCR	12,611	0	157,203	0	169,814

NOTES:

- 1. Data are reported in the table only for paved roads and parking lots that received a condition rating.
- 2. Non-linear roads (MRP collected routes) are measured by area and converted to equivalent route miles based on a 22-ft pavement width in order to be included in the mileage totals for paved roads shown above.
- 3. Quantities in the table above are derived from the route condition data within the PMS_20, PMS_MRL, PMS_MRP, and PMS_PKG tables in the Park geodatabase.

Parkwide Condition Percentages



Road Condition Percentages

Parking Area Condition Percentages

Figure 1: Pavement Condition Rating Breakdown for Paved Roads and Parking Areas

Explanation of the Excellent, Good, Fair, and Poor Condition Descriptions

The Road Inventory Program aims to provide assistance in translating the excellent / good / fair / poor rating categories into pavement needs categories. The PCR can be used to indicate the place in the Pavement Life Cycle and the type of treatments that should be considered now and into the future.

- Excellent / New: PCR of 95-100
 - o Pavements in this range will require only spot repairs
- Good: PCR of 85-94
 - o Pavements in this range will likely be candidates for Preventive Maintenance. Examples include Chip and Slurry Seals, Micro Surfacing and Thin Overlays.
- Fair: PCR of 61-84
 - o Pavements in this range will likely be candidates of Light Rehabilitation (L3R). Examples include singlelift overlays up to 2.5 inches in total thickness, milling and overlays.
- Poor: PCR of 0-60
 - o Pavements in this range will likely be candidates of Heavy Rehabilitation or Reconstruction (H3R or 4R). Examples include Pulverization, Multiple Lift Overlays, and Reconstruction.

CONDITION CATEGORIES AND TREATMENTS EXCELLENT / Localized Repairs Only GOOD / Preventive Maintenance FAIR / Light Rehabilitation POOR / Heavy Rehabilitation Reconstruction Payement Age

At this time, specific Maintenance and Rehabilitation activities should be evaluated and recommended at the project level. Site-specific conditions that influence treatment type should be determined based on performing a subsurface investigation and/or pavement condition survey, and not be based solely on RIP data. Additionally, RIP produces a snapshot of conditions at the time in which the data were collected. For further information or to obtain additional Pavement Management System's data from our Highway Pavement Management Application (HPMA) please contact the Eastern Federal Lands pavement team.



Road Condition Summary Report for Data Collection Vehicle (DCV) Rated Roads

Organ Pipe Cactus National Monument

Condition (Rating / Index) Legend

EXCELLENT (95 - 100)

GOOD (85 - 94) FAIR (61 - 84)

POOR (0 - 60)

NR = NOT RATED

Notes:

- This condition summary report contains only the roads rated with the Data Collection Vehicle (DCV).
- Condition on roads that were manually rated and parking areas are shown in separate reports.
- Additional details on individual road ratings can be found in Section 5 of the Cycle 6 RIP Report.
- Refer to the RIP Report Appendix for an explanation of the rating system and rating methods.

Route-Level Condition for Roads Rated with the Data Collection Vehicle (DCV)						_	5		ex	×	ng	D)	×	
Route No.	FMSS No.	Route Name	Functions Class	ıl Surf. Type	Paved Length (Miles)	Pavement Condition Rating (PCR)	Roughness Condition Index (RCI)	Surface Condition Rating (SCR)	Structural Crack Ind	Alligator Crack Index	Longitudinal Cracking Index	Transverse Cracking Index	Patch / Pothole Index	Rutting Index
ORPI-0010	72387	VISITOR CENTER DRIVE	1	AS	0.34	75	NR	75	96	100	96	75	100	98
ORPI-0100	72452	RESIDENCE ACCESS ROAD	6	AS	1.14	91	NR	91	97	100	97	94	100	91
ORPI-0101	72864	TWIN PEAKS ACCESS ROAD	2	AS	1.32	88	77	95	96	100	96	95	100	98
ORPI-0200	72866	CAMPGROUND LOOP ROAD	3	AS	0.82	88	NR	88	100	100	100	100	99	88
ORPI-0205	72685	MAINTENANCE ACCESS ROAD	5	AS	0.08	90	NR	90	93	100	93	90	100	92
ORPI-0206	102406	CAMPGROUND SITES 1-6 ACCESS	3	AS	0.09	90	NR	90	100	100	100	98	99	90
ORPI-0207	102418	CAMPGROUND SITES 7-15 ACCESS	3	AS	0.12	90	NR	90	100	100	100	99	99	90
ORPI-0208	102419	CAMPGROUND SITES 16-23 ACCESS	3	AS	0.13	84	NR	84	100	100	100	98	97	84
ORPI-0209	102421	CAMPGROUND SITES 24-34 ACCESS	3	AS	0.15	89	NR	89	100	100	100	100	98	89
ORPI-0210	102422	CAMPGROUND SITES 35-45 ACCESS	3	AS	0.16	88	NR	88	100	100	100	99	96	88
ORPI-0211	102424	CAMPGROUND SITES 46-57 ACCESS	3	AS	0.17	82	NR	82	100	100	100	100	94	82
ORPI-0212	102425	CAMPGROUND SITES 58-70 ACCESS	3	AS	0.18	88	NR	88	100	100	100	100	98	88
ORPI-0213	102426	CAMPGROUND SITES 71-85 ACCESS	3	AS	0.19	89	NR	89	100	100	100	100	99	89
ORPI-0214	102427	CAMPGROUND SITES 86-95 ACCESS	3	AS	0.20	90	NR	90	100	100	100	100	99	90
ORPI-0215	102428	CAMPGROUND SITES 96-112 ACCESS	3	AS	0.21	84	NR	84	100	100	100	100	99	84
ORPI-0216	102429	CAMPGROUND SITES 113-128 ACCESS	3	AS	0.21	91	NR	91	100	100	100	100	98	91
ORPI-0217	102430	CAMPGROUND SITES 129-145 ACCESS	3	AS	0.22	82	NR	82	100	100	100	100	97	82
ORPI-0218	102431	CAMPGROUND SITES 146-158 ACCESS	3	AS	0.23	87	NR	87	100	100	100	100	100	87
ORPI-0219	102432	CAMPGROUND SITES 159-174 ACCESS	3	AS	0.23	88	NR	88	100	100	100	100	100	88

Data Collection Date: 01/2017



Road Condition Summary Report for Data Collection Vehicle (DCV) Rated Roads

Organ Pipe Cactus National Monument

Condition (Rating / Index) Legend

GOOD (85 - 94)

FAIR (61 - 84)

POOR (0 - 60)

NR = NOT RATED

Notes:

- This condition summary report contains only the roads rated with the Data Collection Vehicle (DCV).
- Condition on roads that were manually rated and parking areas are shown in separate reports.
- Additional details on individual road ratings can be found in Section 5 of the Cycle 6 RIP Report.
- Refer to the RIP Report Appendix for an explanation of the rating system and rating methods.

Route No.	Route-	Level Condition for Roads Rated with the Data Collection Route Name	Vehicle (DCV) Functional Surf Class Type	-09	Pavement Condition Rating (PCR)	Roughness Condition Index (RCI)	Surface Condition Rating (SCR)	Structural Crack Index	Alligator Crack Index	Longitudinal Cracking Index	Transverse Cracking Index	Patch / Pothole Index	Rutting Index
ORPI-0220	102435	CAMPGROUND SITES 175-191 ACCESS	3 AS	0.25	91	NR	91	100	100	100	100	100	91
ORPI-0221	102434	CAMPGROUND SITES 192-208 ACCESS	3 AS	0.25	87	NR	87	100	100	100	100	100	87
ORPI-0401	72473	SPUR RESIDENCE ROAD WEST	6 AS	0.07	89	NR	89	100	100	100	100	100	89
ORPI-0402	72455	SPUR RESIDENCE ROAD EAST	6 AS	0.09	76	NR	76	100	100	100	98	99	76
ORPI-0403	102994	CAMPGROUND HOUSING ROAD	6 AS	0.05	67	NR	67	100	100	100	100	99	67
ORPI-0409	72870	GROUP CAMPGROUND ACCESS ROAD	3 AS	0.14	97	NR	97	100	100	100	100	100	97

Data Collection Date: 01/2017



Road Condition Summary Report for Manually Rated Roads

Condition (Rating / Index) Legend EXCELLENT (95 - 100) GOOD (85 - 94) FAIR (61 - 84) POOR (0 - 60) NR = NOT RATED

Organ Pipe Cactus National Monument

Notes:

- This condition summary report contains only the roads that were manually rated.
 - o MRL = Manually Rated Line (a linear road)
 - MRP = Manually Rated Polygon (a non-linear road)
- Condition on roads that were rated with the Data Collection Vehicle (DCV) are shown in a separate report.
- A road is manually rated when it is determined to be unsuitable for the DCV to drive.
- Additional details on individual road ratings can be found in Section 5 of the Cycle 6 RIP Report.
- Refer to the RIP Report Appendix for an explanation of the rating system and rating methods.

		Route-Level Condition for Manually Rated Line (MRL) Ro	oads			Paved	nent Co (PCR)	hness Condition (RCI)	ce Condition g (SCR)	ural Crack Index	tor Crack	tudinal Cracking	verse Cracking	/ Pothole Index	g Index
Route No.	FMSS No.	Route Name	Fu	nctional Class	Surf. Type	Length (Miles)	Paver Rating	Rougl Index	Surfac Rating	Struct	Alliga	Longit Index	Trans Index	Patch	Rottin
ORPI-0011	74168	AJO MOUNTAIN DRIVE		1	AS	3.18	82	NR	82	93	88	90	88	82	87
ORPI-0012	74253	PUERTO BLANCO DRIVE		1	AS	1.68	76	NR	76	82	100	82	76	100	99
ORPI-0408	72482	100 K WATER TANK ROAD		6	AS	0.10	53	NR	53	NR	73	53	53	73	90



Parking Area Condition Summary Report

Organ Pipe Cactus National Monument

EXCELLENT (97) GOOD (90) FAIR (73) POOR* (0, 30, 53) NR = NOT RATED

Condition (Rating / Index) Legend

Notes:

- A PCR of 0 indicates a paved parking area in very poor condition. Individual distresses could not be identified.
- Additional details on individual parking areas can be found in Section 6 of the Cycle 6 RIP Report.
- Refer to the RIP Report Appendix for an explanation of the rating system and rating methods.

							<u>Asphalt Surface Distresses</u>				Concrete Surface Distresse						
Route No.	FMSS No.	Condition Rating Details for Parking Areas Route Name	User Access	Surf. Type	Area (Sq. Ft.)	Pavement Condition Rating (PCR)	Alligator Cracking	Longitudinal / Tranverse Cracking	Rutting / Distortions	Potholes / Patching	HMA Patching	Surface Raveling / Bleeding	Joint Faulting	Slab Cracking	Joint Distresses	Delamination / Pop-Outs	Potholes / Patching
ORPI-0903	72690	MAINTENANCE YARD	NONPUBLIC	AS	33,594	90	97	90	90	97	97	90					
ORPI-0904A	72424	VISITOR CENTER PARKING A	PUBLIC	AS	36,266	90	97	90	90	97	97	90					
ORPI-0904B	105672	VISITOR CENTER PARKING B	PUBLIC	AS	8,145	90	97	90	97	97	97	90					
ORPI-0905	102991	OFFICE PARKING	NONPUBLIC	AS	7,277	90	97	90	97	97	97	97					
ORPI-0906	102987	GROUP CAMPGROUND PARKING	PUBLIC	AS	12,611	53	73	53	90	90	97	90					
ORPI-0907	102774	CAMPGROUND PARKING	PUBLIC	AS	995	90	97	97	97	97	97	90					
ORPI-0908	102436	DUMP STATION LOOP	PUBLIC	AS	7,621	90	97	90	97	97	90	97					
ORPI-0909	102773	CAMPGROUND HOUSING PARKING	NONPUBLIC	AS	2,638	90	97	90	90	97	97	97					
ORPI-0910	109708	TILLOTSON PEAK WAYSIDE PARKING	PUBLIC	AS	28,505	90	90	90	90	97	97	90					
ORPI-0911	109712	AJO MOUNTAINS WAYSIDE PARKING	PUBLIC	AS	30,415	90	90	90	90	97	97	90					
ORPI-0912	11 <i>5</i> 98 <i>7</i>	HOUSING AREA DUPLEX HOUSING PARKING	NONPUBLIC	AS	1,747	90	97	90	90	97	97	90					


Data Collection Date: 01/2016

Section 4 Park Route Location Maps






ROUTE LOCATION MAP Key Map




NPS Collected Routes Unpaved NPS Routes (Not Collected) —— Non-NPS Collected Routes






ROUTE LOCATION MAP Map 1



Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community

Note: Unique colors are used to differentiate roads



ROUTE LOCATION MAP Map 1A




Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community

Note: Unique colors are used to differentiate roads

	Miles	
0	0.25	0.5

ROUTE LOCATION MAP Map 1B




Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community


Note: Unique colors are used to differentiate roads

	Mi	iles	
0	0.2	25 0.5	5

ROUTE CONDITION MAP PCR - MILE BY MILE Key Map




Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community




	Miles	
0	10	20



ROUTE CONDITION MAP PCR - MILE BY MILE Area Map 1




Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community




Miles
10 20




ROUTE CONDITION MAP PCR - MILE BY MILE Area Map 1A




Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community






ROUTE CONDITION MAP PCR - MILE BY MILE Area Map 1B



Sources: Esri, HERE, DeLorme, USGS, Intermap, increment P Corp., NRCAN, Esri Japan, METI, Esri China (Hong Kong), Esri (Thailand), TomTom, MapmyIndia, © OpenStreetMap contributors, and the GIS User Community



	Miles	
)	0.25	0.5


Section 5 Paved Road Condition Rating Sheets





ROUTE 0010: VISITOR CENTER DRIVE

Data Collection Vehicle (DCV) Rating




Sources: Esri, DeLorme, NAVTEQ, TomTom, Intermap, increment P Corp., GEBCO, USGS, FAO, NPS, NRCAN, GeoBase, IGN, Kadaster NL, Ordnance Survey, Esri Japan, METI, Esri China (Hong Kong), swisstopo, and the GIS User Community

	Route (Condition Legend – Pay	vement Cond	ition Rating (PCR)			
Poor (0 - 60)	Fair (6		(85 - 94)			Not Rated		
		See Appendix for de	finitions and f	ormulas				
Inspection Date: 1	/11/2017	Beginning Section MP	0					
Paved Length (Miles): 0.34		Section Length (MI)	0.34					
Surface Type: A	SPHALT	Route Summary				•		
Roadway Condition Information								
Pavement Condition Rat	ting (PCR)	75	75					
Surface Condition Rating	(SCR)	75	75					
Roughness Condition Index (RCI)		N/A	N/A					
Distress Index Values								
Structural Crack Index		96	96					
Alligator Crack Index		100	100					
Longitudinal Crack Index		96	96					
Transverse Cracking Inc	lex	75	75					
Patching Index		100	100					
Rutting Index		98	98					
International Roughness Index (IRI)		N/A	N/A					
Lane & Width Information								
Number of Lanes		2	2					
Paved Width (ft)		25.6	25.6					
Lane Width (ft)		10.3	10.3					

ROUTE 0011: AJO MOUNTAIN DRIVE

Manual Rating



Sources: Esri, DeLorme, NAVTEQ, TomTom, Intermap, increment P Corp., GEBCO, USGS, FAO, NPS, NRCAN, GeoBase, IGN, Kadaster NL, Ordnance Survey, Esri Japan, METI, Esri China (Hong Kong), swisstopo, and the GIS User Community

Route Condition Legend – Pavement Condition Rating (PCR)									
Poor (0 - 60)	Fair (6)	Good (85 - 94) Exc	cellent (95 - 100) Not Rated						
See Appendix for definitions and formulas									
Inspection Date:	1/26/2016	0 1 pu , cu 2 cu gui	Overall PCR: 82						
Paved Length (Miles): 3.18 *		(Miles): 14.87							
Surface Type:	ASPHALT								

^{*} Manually Rated 2.64 miles out of the 3.18 paved miles because low water crossings were not rated.

Organ Pipe Cactus National Monument ROUTE 0011: AJO MOUNTAIN DRIVE

Inspection Date: January 26, 2016

Section	Begin	End	Section	Paved	Surface	Pavement Condition	Structural	Alligator	Longitudinal	Transverse Cracking	Patching	Rutting
Number	Milepost	Milepost	Length	Width	Type	Rating (PCR)	Crack Index	Crack Index	Crack Index	Index	Index	Index
1	0.00	0.21	0.21	N/A	GRAVEL	Not Rated						
LWC	0.21	0.22	0.01	N/A	CONCRETE	Not Rated						
2	0.22	0.44	0.22	N/A	GRAVEL	Not Rated						
LWC	0.44	0.45	0.01	N/A	CONCRETE	Not Rated						
3	0.45	0.62	0.17	N/A	GRAVEL	Not Rated						
LWC	0.62	0.63	0.01	N/A	CONCRETE	Not Rated						
4	0.63	0.79	0.16	N/A	GRAVEL	Not Rated						
LWC 5	0.79	0.80 1.01	0.01 0.21	N/A N/A	CONCRETE GRAVEL	Not Rated Not Rated						
LWC*	0.80 1.02	1.01	0.21	N/A N/A	CONCRETE	Not Rated Not Rated						
6	1.02	2.00	0.01	N/A	GRAVEL	Not Rated						
LWC*	2.00	2.02	0.02	N/A	CONCRETE	Not Rated						
7	2.03	2.35	0.32	N/A	GRAVEL	Not Rated						
LWC*	2.35	2.37	0.02	N/A	CONCRETE	Not Rated						
8	2.38	3.08	0.71	N/A	GRAVEL	Not Rated						
LWC	3.08	3.10	0.01	N/A	CONCRETE	Not Rated						
9	3.10	5.76	2.66	N/A	GRAVEL	Not Rated						
10	5.76	5.86	0.10	N/A	ASPHALT	30	30	73	53	90	30	53
11	5.86	6.36	0.50	N/A	ASPHALT	91	94	99	95	91	100	96
12	6.36	6.44	0.08	N/A	ASPHALT	92	97	99	98	92	100	100
LWC 13	6.44 6.46	6.46 6.86	0.01 0.41	N/A N/A	ASPHALT	Not Rated 92	97	99	98	92	100	100
14	6.86	7.36	0.41	N/A	ASPHALT	92 91	94	99	95	92 91	100	100
15	7.36	7.46	0.10	N/A	ASPHALT	30	30	53	73	90	30	53
16	7.46	7.66	0.20	N/A	ASPHALT	92	92	100	92	94	100	100
17	7.66	7.89	0.23	N/A	ASPHALT	30	30	53	73	90	30	53
LWC*	7.89	7.89	0.01	N/A	CONCRETE	Not Rated						
18	7.95	8.31	0.36	N/A	GRAVEL	Not Rated						
LWC*	8.32	8.32	0.00	N/A	CONCRETE	Not Rated						
19	8.34	8.63	0.30	N/A	GRAVEL	Not Rated						
LWC*	8.75	8.76	0.01	N/A	CONCRETE	Not Rated						
20	8.77	9.47	0.70	N/A	GRAVEL	Not Rated						
21*	9.51	9.53	0.02	N/A	GRAVEL	Not Rated						
22* 23	9.59	10.37 10.52	0.78 0.15	N/A	GRAVEL	Not Rated	N/A	N/A	N/A	N/A	N/A	N/A
23	10.37 10.52	10.52	0.15	N/A N/A	ASPHALT ASPHALT	0 43	N/A 80	100	N/A 80	N/A 43	100	100
25	10.32	16.70	5.54	N/A	GRAVEL	Not Rated	30	100	50	7.3	100	100
LWC*	16.25	16.26	0.01	N/A	CONCRETE	Not Rated						
26	16.28	16.79	0.51	N/A	GRAVEL	Not Rated						
27	16.79	16.98	0.20	N/A	ASPHALT	30	30	53	97	97	30	53
28	16.98	17.55	0.57	N/A	GRAVEL	Not Rated						
LWC*	17.56	17.57	0.01	N/A	CONCRETE	Not Rated						
29	17.58	18.05	0.47	N/A	GRAVEL	Not Rated						

NOTES:

Only the paved sections received a condition rating. The route was manually rated in order to keep the data collection vehicle (DCV) off of the rough, unpaved road sections. Roughness is not measured when taking a manual rating.

 $LWC = concrete \ low \ water \ crossings \ were \ not \ rated, \ but \ locations \ are \ noted \ in \ the \ table \ above.$

 LWC^* = these low water crossings have very short asphalt sections before and after the concrete portions. These asphalt sections were not factored into the pavement condition rating due to their very short length.

ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 10 (5.76 MP To 5.86 MP)



ORPI_0011_MP 5.76-5.86_3151.JPG



ORPI_0011_MP 5.76-5.86_3153.JPG



ORPI_0011_MP 5.76-5.86_3155.JPG



ORPI_0011_MP 5.76-5.86_3152.JPG



ORPI_0011_MP 5.76-5.86_3154.JPG



ORPI_0011_MP 5.76-5.86_3156.JPG

Organ Pipe Cactus National Monument ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 11 (5.86 MP To 6.36 MP) and Section 12 (6.36 MP To 6.44 MP)





ORPI_0011_MP 5.86-6.36_3159.JPG



ORPI_0011_MP 6.36-6.44_3161.JPG



ORPI_0011_MP 5.86-6.36_3158.JPG



ORPI_0011_MP 6.36-6.44_3160.JPG



ORPI_0011_MP 6.36-6.44_3162.JPG

Organ Pipe Cactus National Monument ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 13 (6.46 MP To 6.86 MP) and Section 14 (6.86 MP To 7.36 MP)





ORPI_0011_MP 6.46-6.86_3165.JPG



ORPI_0011_MP 6.86-7.36_3167.JPG



ORPI_0011_MP 6.46-6.86_3164.JPG



ORPI_0011_MP 6.86-7.36_3166.JPG



ORPI_0011_MP 6.86-7.36_3168.JPG

ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 15 (7.36 MP To 7.46 MP) and Section 16 (7.46 MP To 7.66 MP)



ORPI_0011_MP 7.36-7.46_3170.JPG



ORPI_0011_MP 7.36-7.46_3172.JPG



ORPI_0011_MP 7.46-7.66_3174.JPG



ORPI_0011_MP 7.36-7.46_3171.JPG



ORPI_0011_MP 7.46-7.66_3173.JPG



ORPI_0011_MP 7.46-7.66_3175.JPG

Organ Pipe Cactus National Monument ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 17 (7.66 MP To 7.89 MP) and Section 23 (10.37 MP To 10.52 MP)



ORPI_0011_MP 7.66-7.89_3177.JPG



ORPI_0011_MP 7.66-7.89_3178.JPG



ORPI_0011_MP 7.66-7.89_3179.JPG



ORPI_0011_MP 10.37-10.52_3202.JPG



ORPI_0011_MP 10.37-10.52_3203.JPG



ORPI_0011_MP 10.37-10.52_3204.JPG

Organ Pipe Cactus National Monument ROUTE 0011: AJO MOUNTAIN DRIVE

Condition Photos Section 24 (10.52 MP To 10.70 MP) and Section 27 (16.79 MP To 16.98 MP)



ORPI_0011_MP 10.52-10.70_3205.JPG



ORPI_0011_MP 10.52-10.70_3207.JPG



ORPI_0011_MP 16.79-16.98_3214.JPG



ORPI_0011_MP 10.52-10.70_3206.JPG




ORPI_0011_MP 16.79-16.98_3213.JPG



ORPI_0011_MP 16.79-16.98_3215.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Manual Rating



	Route C	Condition Legend – Pavement Condition	Rating (PCR)
Poor (0 - 60)	Fair (61	Good (85 - 94) Exc	cellent (95 - 100) Not Rated
	_	See Appendix for definitions and formula	las
Inspection Date:	1/26/2016	enparea zengen	Total PCR: 76
Paved Length (Miles)	: 1.68	(Miles): 35.58	
Surface Type:	ASPHALT		

ROUTE 0012: PUERTO BLANCO DRIVE

Inspection Date: January 26, 2016

Section Number	Begin Milepost	End Milepost	Section Length	Paved Width	Surface Type	Pavement Condition Rating (PCR)	Structural Crack Index	Alligator Crack Index	Longitudinal Crack Index	Transverse Cracking Index	Patching Index	Rutting Index
1	0.00	0.50	0.50	N/A	GRAVEL	Not Rated						
2	0.50	0.65	0.15	25	ASPHALT	83	83	100	83	84	100	100
3	0.65	1.05	0.40	N/A	GRAVEL	Not Rated						
4	1.05	1.13	0.08	24	ASPHALT	66	66	100	66	84	100	100
5	1.13	1.24	0.11	N/A	GRAVEL	Not Rated						
6	1.24	1.42	0.18	23	ASPHALT	83	84	100	84	83	100	100
7	1.42	1.65	0.22	N/A	GRAVEL	Not Rated						
8	1.65	1.75	0.10	23	ASPHALT	61	73	100	73	61	100	100
9	1.75	1.91	0.16	N/A	GRAVEL	Not Rated						
10	1.91	2.00	0.09	24	ASPHALT	71	87	99	88	71	100	100
11	2.00	2.05	0.05	N/A	GRAVEL	Not Rated						
12	2.05	2.15	0.11	24	ASPHALT	73	97	100	97	73	100	100
13	2.15	2.25	0.09	N/A	GRAVEL	Not Rated						
14	2.25	2.32	0.08	24	ASPHALT	86	86	100	86	88	100	100
15	2.32	2.89	0.57	N/A	GRAVEL	Not Rated						
16	2.89	3.04	0.16	24	ASPHALT	75	92	100	92	75	100	100
17	3.04	3.10	0.05	N/A	GRAVEL	Not Rated						
18	3.10	3.12	0.03	20	ASPHALT	55	55	100	55	88	100	100
19	3.12	3.19	0.07	N/A	GRAVEL	Not Rated						
20	3.19	3.30	0.11	22	ASPHALT	72	88	100	88	72	100	100
21	3.30	3.46	0.16	N/A	GRAVEL	Not Rated						
22	3.46	3.56	0.10	22	ASPHALT	81	81	100	81	87	100	100
23	3.56	3.73	0.17	N/A	GRAVEL	Not Rated						
24	3.73	3.79	0.06	20	ASPHALT	69	75	100	75	69	100	100
25	3.79	3.89	0.10	N/A	GRAVEL	Not Rated						
26	3.89	4.08	0.19	22	ASPHALT	74	80	100	80	74	100	100
27	4.08	4.15	0.07	N/A	GRAVEL	Not Rated						
28	4.15	4.20	0.05	22	ASPHALT	75	75	100	75	77	100	100
29	4.20	4.27	0.06	N/A	GRAVEL	Not Rated						
30	4.27	4.38	0.12	22	ASPHALT	69	73	100	73	69	100	100
31	4.38	4.42	0.03	N/A	GRAVEL	Not Rated						
32	4.42	4.49	0.08	22	ASPHALT	73	93	100	93	73	100	100
33	4.49	37.26	32.77	N/A	GRAVEL	Not Rated						

NOTE: Only the paved sections received a condition rating. The route was manually rated in order to keep the data collection vehicle (DCV) off of the rough, unpaved road sections. Roughness is not measured when taking a manual rating. Low water crossings were not collected for route 0012.

Condition Photos Section 2 (0.50 MP To 0.65 MP)



ORPI_0012_MP 0.50-0.65_3043.JPG



ORPI_0012_MP 0.50-0.65_3045.JPG



ORPI_0012_MP 0.50-0.65_3047.JPG



ORPI_0012_MP 0.50-0.65_3044.JPG



ORPI_0012_MP 0.50-0.65_3046.JPG




ORPI_0012_MP 0.50-0.65_3048.JPG

Condition Photos Section 4 (1.05 MP To 1.13 MP)



ORPI_0012_MP 1.05-1.13_3049.JPG



ORPI_0012_MP 1.05-1.13_3051.JPG



ORPI_0012_MP 1.05-1.13_3053.JPG



ORPI_0012_MP 1.05-1.13_3050.JPG



ORPI_0012_MP 1.05-1.13_3052.JPG




ORPI_0012_MP 1.05-1.13_3054.JPG

G W D


Condition Photos Section 6 (1.24 MP To 1.42 MP)



ORPI_0012_MP 1.24-1.42_3055.JPG



ORPI_0012_MP 1.24-1.42_3056.JPG



ORPI_0012_MP 1.24-1.42_3057.JPG



ORPI_0012_MP 1.24-1.42_3058.JPG



ORPI_0012_MP 1.24-1.42_3059.JPG



ORPI_0012_MP 1.24-1.42_3060.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 8 (1.65 MP To 1.75 MP)



ORPI_0012_MP 1.65-1.75_3061.JPG



ORPI_0012_MP 1.65-1.75_3063.JPG



ORPI_0012_MP 1.65-1.75_3065.JPG



ORPI_0012_MP 1.65-1.75_3062.JPG



ORPI_0012_MP 1.65-1.75_3064.JPG



ORPI_0012_MP 1.65-1.75_3066.JPG

Condition Photos Section 10 (1.91 MP To 2.00 MP)



ORPI_0012_MP 1.91-2.00_3067.JPG



ORPI_0012_MP 1.91-2.00_3068.JPG



ORPI_0012_MP 1.91-2.00_3069.JPG



ORPI_0012_MP 1.91-2.00_3070.JPG



ORPI_0012_MP 1.91-2.00_3071.JPG



ORPI_0012_MP 1.91-2.00_3072.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 12 (2.05 MP To 2.15 MP)



ORPI_0012_MP 2.05-2.15_3073.JPG



ORPI_0012_MP 2.05-2.15_3074.JPG



ORPI_0012_MP 2.05-2.15_3075.JPG



ORPI_0012_MP 2.05-2.15_3076.JPG



ORPI_0012_MP 2.05-2.15_3077.JPG



ORPI_0012_MP 2.05-2.15_3078.JPG

Condition Photos

Section 14 (2.25 MP To 2.32 MP)



ORPI_0012_MP 2.25-2.32_3079.JPG



ORPI_0012_MP 2.25-2.32_3081.JPG



ORPI_0012_MP 2.25-2.32_3083.JPG



ORPI_0012_MP 2.25-2.32_3080.JPG



ORPI_0012_MP 2.25-2.32_3082.JPG



ORPI_0012_MP 2.25-2.32_3084.JPG

Condition Photos Section 16 (2.89 MP To 3.04 MP)



ORPI_0012_MP 2.89-3.04_3085.JPG



ORPI_0012_MP 2.89-3.04_3086.JPG



ORPI_0012_MP 2.89-3.04_3087.JPG



ORPI_0012_MP 2.89-3.04_3088.JPG



ORPI_0012_MP 2.89-3.04_3089.JPG



ORPI_0012_MP 2.89-3.04_3090.JPG

Condition Photos Section 18 (3.10 MP To 3.12 MP)





ORPI_0012_MP 3.10-3.12_3093.JPG



ORPI_0012_MP 3.10-3.12_3095.JPG



ORPI_0012_MP 3.10-3.12_3092.JPG



ORPI_0012_MP 3.10-3.12_3094.JPG



ORPI_0012_MP 3.10-3.12_3096.JPG

Condition Photos Section 20 (3.19 MP To 3.30 MP)





ORPI_0012_MP 3.19-3.30_3099.JPG



ORPI_0012_MP 3.19-3.30_3101.JPG



ORPI_0012_MP 3.19-3.30_3098.JPG



ORPI_0012_MP 3.19-3.30_3100.JPG



ORPI_0012_MP 3.19-3.30_3102.JPG


Condition Photos Section 22 (3.46 MP To 3.56 MP)



ORPI_0012_MP 3.46-3.56_3103.JPG



ORPI_0012_MP 3.46-3.56_3104.JPG



ORPI_0012_MP 3.46-3.56_3105.JPG



ORPI_0012_MP 3.46-3.56_3106.JPG



ORPI_0012_MP 3.46-3.56_3107.JPG



ORPI_0012_MP 3.46-3.56_3108.JPG

Condition Photos Section 24 (3.73 MP To 3.79 MP)



ORPI_0012_MP 3.73-3.79_3109.JPG



ORPI_0012_MP 3.73-3.79_3111.JPG



ORPI_0012_MP 3.73-3.79_3113.JPG



ORPI_0012_MP 3.73-3.79_3110.JPG



ORPI_0012_MP 3.73-3.79_3112.JPG



ORPI_0012_MP 3.73-3.79_3114.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 26 (3.89 MP To 4.08 MP)



ORPI_0012_MP 3.89-4.08_3115.JPG





ORPI_0012_MP 3.89-4.08_3117.JPG



ORPI_0012_MP 3.89-4.08_3118.JPG



ORPI_0012_MP 3.89-4.08_3119.JPG



ORPI_0012_MP 3.89-4.08_3120.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 28 (4.15 MP To 4.20 MP)



ORPI_0012_MP 4.15-4.20_3121.JPG



ORPI_0012_MP 4.15-4.20_3123.JPG



ORPI_0012_MP 4.15-4.20_3125.JPG



ORPI_0012_MP 4.15-4.20_3122.JPG



ORPI_0012_MP 4.15-4.20_3124.JPG



ORPI_0012_MP 4.15-4.20_3126.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 30 (4.27 MP To 4.38 MP)



ORPI_0012_MP 4.27-4.38_3127.JPG



ORPI_0012_MP 4.27-4.38_3128.JPG



ORPI_0012_MP 4.27-4.38_3129.JPG



ORPI_0012_MP 4.27-4.38_3130.JPG



ORPI_0012_MP 4.27-4.38_3131.JPG



ORPI_0012_MP 4.27-4.38_3132.JPG

ROUTE 0012: PUERTO BLANCO DRIVE

Condition Photos Section 32 (4.42 MP To 4.49 MP)



ORPI_0012_MP 4.42-4.49_3133.JPG



ORPI_0012_MP 4.42-4.49_3134.JPG



ORPI_0012_MP 4.42-4.49_3135.JPG



ORPI_0012_MP 4.42-4.49_3136.JPG




ORPI_0012_MP 4.42-4.49_3137.JPG



ORPI_0012_MP 4.42-4.49_3138.JPG

ROUTE 0100: RESIDENCE ACCESS ROAD


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	tion Rating (PCR)	
Poor (0 - 60			(85 - 94)	Excellent (Not Rated
		See Appendix for def	finitions and f	ormulas		
Inspection Date:	1/11/2017	Beginning Section MP	0	1		
Paved Length (Mile	es): 1.14	Section Length (MI)	1	0.14		
Surface Type:	ASPHALT	Route Summary				
Roadway Condition	Information					
Pavement Conditio	n Rating (PCR)	91	91	95		
Surface Condition R	ating (SCR)	91	91	95		
Roughness Condition	n Index (RCI)	N/A	N/A	N/A		
Distress Index Valu	es					
Structural Crack In-	dex	97	96	100		
Alligator Crack Ind	lex	100	100	100		
Longitudinal Crack	Index	97	96	100		
Transverse Crackin	g Index	94	93	100		
Patching Index		100	100	100		
Rutting Index		91	91	95		
International Rough	nness Index (IRI)	N/A	N/A	N/A		
Lane & Width Info	rmation					
Number of Lanes		2	2	2		
Paved Width (ft)		20.3	20.5	18.8		
Lane Width (ft)		9.7	9.7	9.4		

ROUTE 0101: TWIN PEAKS ACCESS ROAD


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	tion Rating (PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	85 - 94) Excellent (95 - 100)		Not Rate	ed
		See Appendix for de	finitions and f	ormulas			
Inspection Date: 1	/11/2017	Beginning Section MP	0	1			
Paved Length (Miles): 1	.32	Section Length (MI)	1	0.32			
Surface Type:	ASPHALT	Route Summary					
Roadway Condition Info	ormation						
Pavement Condition Ra	ting (PCR)	88	87	87			
Surface Condition Rating	g (SCR)	95	93	98			
Roughness Condition Ind	lex (RCI)	77	79	70			
Distress Index Values							
Structural Crack Index		96	95	99			
Alligator Crack Index		100	100	100			
Longitudinal Crack Inde	ex	96	95	99			
Transverse Cracking Inc	dex	95	93	99			
Patching Index		100	100	100			
Rutting Index		98	98	98			
International Roughness	s Index (IRI)	177	171	203			
Lane & Width Informat	tion						
Number of Lanes		2	2	2			
Paved Width (ft)		24.3	24.2	24.5			
Lane Width (ft)		10	10.1	9.8			

ROUTE 0200: CAMPGROUND LOOP ROAD


Data Collection Vehicle (DCV) Rating



Rout	e Condition Legend – Pav	ement Cond	lition Rating (PCR)	
		(85 - 94)	Excellent (95 - 100)	Not Rated
	See Appendix for def	finitions and	formulas	
Inspection Date: 1/11/2017	Beginning Section MP	0		
Paved Length (Miles): 0.82	Section Length (MI)	0.82		
Surface Type: ASPHALT	Route Summary			
Roadway Condition Information				
Pavement Condition Rating (PCR)	88	88		
Surface Condition Rating (SCR)	88	88		
Roughness Condition Index (RCI)	N/A	N/A		
Distress Index Values				
Structural Crack Index	100	100		
Alligator Crack Index	100	100		
Longitudinal Crack Index	100	100		
Transverse Cracking Index	100	100		
Patching Index	99	99		
Rutting Index	88	88		
International Roughness Index (IRI)	N/A	N/A		
Lane & Width Information				
Number of Lanes	1	1		
Paved Width (ft)	13.6	13.6		
Lane Width (ft)	13.6	13.6		

ROUTE 0205: MAINTENANCE ACCESS ROAD


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	ition Rating (PCR)		
Poor (0 - 60			(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for def	finitions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Mile	es): 0.08	Section Length (MI)	0.08				
Surface Type:	ASPHALT	Route Summary					
Roadway Condition	n Information						
Pavement Condition	on Rating (PCR)	90	90				
Surface Condition R	Rating (SCR)	90	90				
Roughness Condition	on Index (RCI)	N/A	N/A				
Distress Index Valu	es						
Structural Crack In	ıdex	93	93				
Alligator Crack Inc	dex	100	100				
Longitudinal Crack	c Index	93	93				
Transverse Crackir	ng Index	90	90				
Patching Index		100	100				
Rutting Index		92	92				
International Roug	hness Index (IRI)	N/A	N/A				
Lane & Width Info	rmation						
Number of Lanes		2	2				
Paved Width (ft)		21.7	21.7				
Lane Width (ft)		11.8	11.8				

ROUTE 0206: CAMPGROUND SITES 1-6 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pa	vement Cond	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		1 (85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	efinitions and f	formulas			
Inspection Date: 1/	11/2017	Beginning Section M	P 0				
Paved Length (Miles): 0.0	09	Section Length (MI)	0.09				
Surface Type: AS	SPHALT	Route Summary		•			
Roadway Condition Info	rmation						
Pavement Condition Rati	ing (PCR)	90	90				
Surface Condition Rating	(SCR)	90	90				
Roughness Condition Inde	x (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Index	X	100	100				
Transverse Cracking Inde	ex	98	98				
Patching Index		99	99				
Rutting Index		90	90				
International Roughness	Index (IRI)	N/A	N/A				
Lane & Width Informati	on						
Number of Lanes		1	1				
Paved Width (ft)		12.8	12.8				
Lane Width (ft)		12.8	12.8				

ROUTE 0207: CAMPGROUND SITES 7-15 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – F	Pavement Cond	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		od (85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for	definitions and	formulas			
Inspection Date: 1/	11/2017	Beginning Section N	AP 0				
Paved Length (Miles): 0.	12	Section Length (MI	0.12				
Surface Type: AS	SPHALT	Route Summary				•	
Roadway Condition Info	rmation						
Pavement Condition Rati	ing (PCR)	90	90				
Surface Condition Rating	(SCR)	90	90				
Roughness Condition Inde	x (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Index	X	100	100				
Transverse Cracking Inde	ex	99	99				
Patching Index		99	99				
Rutting Index		90	90				
International Roughness	Index (IRI)	N/A	N/A				
Lane & Width Informati	on						
Number of Lanes		1	1				
Paved Width (ft)		11.3	11.3				
Lane Width (ft)		11.3	11.3				

ROUTE 0208: CAMPGROUND SITES 16-23 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	tion Rating (PCR)		
Poor (0 - 60)			(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for det	initions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles)): 0.13	Section Length (MI)	0.13				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition 1	Information						
Pavement Condition	Rating (PCR)	84	84				
Surface Condition Rat	ting (SCR)	84	84				
Roughness Condition	Index (RCI)	N/A	N/A				
Distress Index Values	S						
Structural Crack Inde	ex	100	100				
Alligator Crack Inde	X	100	100				
Longitudinal Crack I	ndex	100	100				
Transverse Cracking	Index	98	98				
Patching Index		97	97				
Rutting Index		84	84				
International Roughn	ness Index (IRI)	N/A	N/A				
Lane & Width Inform	nation						
Number of Lanes		1	1				
Paved Width (ft)		10.7	10.7				
Lane Width (ft)		10.7	10.7				

ROUTE 0209: CAMPGROUND SITES 24-34 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pa	vement Cond	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	efinitions and f	formulas			
Inspection Date: 1	/11/2017	Beginning Section MI	P 0				
Paved Length (Miles): 0	.15	Section Length (MI)	0.15				
Surface Type:	SPHALT	Route Summary				•	
Roadway Condition Info	ormation						
Pavement Condition Ra	ting (PCR)	89	89				
Surface Condition Rating	(SCR)	89	89				
Roughness Condition Ind	lex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inde	ex	100	100				
Transverse Cracking Inc	dex	100	100				
Patching Index		98	98				
Rutting Index		89	89				
International Roughness	s Index (IRI)	N/A	N/A				
Lane & Width Informat	tion						
Number of Lanes		1	1				
Paved Width (ft)		11.1	11.1				
Lane Width (ft)		11.1	11.1				

ROUTE 0210: CAMPGROUND SITES 35-45 ACCESS

Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pa	vement Cond	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		1 (85 - 94)				ted
	·	See Appendix for de		ormulas			
Inspection Date: 1/	11/2017	Beginning Section M	P 0				
Paved Length (Miles): 0.	16	Section Length (MI)	0.16				
Surface Type: A	SPHALT	Route Summary				•	
Roadway Condition Info	rmation						
Pavement Condition Rat	ing (PCR)	88	88				
Surface Condition Rating	(SCR)	88	88				
Roughness Condition Inde	ex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inde	X	100	100				
Transverse Cracking Ind	ex	99	99				
Patching Index		96	96				
Rutting Index		88	88				
International Roughness	Index (IRI)	N/A	N/A				
Lane & Width Informati	on						
Number of Lanes		1	1				
Paved Width (ft)		11	11				
Lane Width (ft)		11	11				

ROUTE 0211: CAMPGROUND SITES 46-57 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pa	vement Cond	ition Rating (I	PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	finitions and f	Formulas			
Inspection Date:	1/11/2017	Beginning Section MI	0				
Paved Length (Miles): (0.17	Section Length (MI)	0.17				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition Inf	formation						
Pavement Condition Ra	ating (PCR)	82	82				
Surface Condition Rating	g (SCR)	82	82				
Roughness Condition Inc	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Ind	lex	100	100				
Transverse Cracking In	dex	100	100				
Patching Index		94	94				
Rutting Index		82	82				
International Roughnes	s Index (IRI)	N/A	N/A				
Lane & Width Informa	tion						
Number of Lanes		1	1				
Paved Width (ft)		10.8	10.8				
Lane Width (ft)		10.8	10.8				

ROUTE 0212: CAMPGROUND SITES 58-70 ACCESS


Data Collection Vehicle (DCV) Rating



Route Condition Legend – Pavement Condition Rating (PCR)										
Poor (0 - 60) Fair (61				Excellent (95 - 100)		Not Rated				
		See Appendix for de	,	ormulas						
Inspection Date:	1/11/2017	Beginning Section MP	0							
Paved Length (Miles): 0.18		Section Length (MI)	0.18							
Surface Type:	ASPHALT	Route Summary				•				
Roadway Condition Information										
Pavement Condition Rating (PCR)		88	88							
Surface Condition Rating (SCR)		88	88							
Roughness Condition Index (RCI)		N/A	N/A							
Distress Index Values										
Structural Crack Index		100	100							
Alligator Crack Index		100	100							
Longitudinal Crack Index		100	100							
Transverse Cracking Index		100	100							
Patching Index		98	98							
Rutting Index		88	88							
International Roughness Index (IRI)		N/A	N/A							
Lane & Width Information										
Number of Lanes		1	1							
Paved Width (ft)		11.1	11.1							
Lane Width (ft)		11.1	11.1							

ROUTE 0213: CAMPGROUND SITES 71-85 ACCESS


Data Collection Vehicle (DCV) Rating



Route Condition Legend – Pavement Condition Rating (PCR)										
Poor (0 - 60) Fair (61				Excellent (95 - 100)		Not Rated				
, ,		See Appendix for de		ormulas						
Inspection Date: 1	/11/2017	Beginning Section MI	0							
Paved Length (Miles): 0.19		Section Length (MI)	0.19							
Surface Type:	ASPHALT	Route Summary				•				
Roadway Condition Information										
Pavement Condition Rating (PCR)		89	89							
Surface Condition Rating (SCR)		89	89							
Roughness Condition Index (RCI)		N/A	N/A							
Distress Index Values										
Structural Crack Index		100	100							
Alligator Crack Index		100	100							
Longitudinal Crack Index		100	100							
Transverse Cracking Index		100	100							
Patching Index		99	99							
Rutting Index		89	89							
International Roughness Index (IRI)		N/A	N/A							
Lane & Width Information							·			
Number of Lanes		1	1							
Paved Width (ft)		10.8	10.8							
Lane Width (ft)		10.8	10.8							

ROUTE 0214: CAMPGROUND SITES 86-95 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Cond	ition Rating (PCR)		
Poor (0 - 60)			(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	,	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles)): 0.2	Section Length (MI)	0.2				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition 1	Information						
Pavement Condition	Rating (PCR)	90	90				
Surface Condition Rat	ing (SCR)	90	90				
Roughness Condition	Index (RCI)	N/A	N/A				
Distress Index Values	S						
Structural Crack Inde	ex	100	100				
Alligator Crack Index	X	100	100				
Longitudinal Crack I	ndex	100	100				
Transverse Cracking	Index	100	100				
Patching Index		99	99				
Rutting Index		90	90				
International Roughn	ness Index (IRI)	N/A	N/A				
Lane & Width Inform	nation						
Number of Lanes		1	1				
Paved Width (ft)		10.8	10.8				
Lane Width (ft)		10.8	10.8				

ROUTE 0215: CAMPGROUND SITES 96-112 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	vement Condi	ition Rating (P	CR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9:		Not Rat	ted
		See Appendix for de	, ,	ormulas			
Inspection Date:	1/11/2017	Beginning Section MF	0				
Paved Length (Miles):	0.21	Section Length (MI)	0.21				
Surface Type:	ASPHALT	Route Summary					
Roadway Condition In	formation						
Pavement Condition R	ating (PCR)	84	84				
Surface Condition Ratin	g (SCR)	84	84				
Roughness Condition In	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inc	lex	100	100				
Transverse Cracking Ir	ndex	100	100				
Patching Index		99	99				
Rutting Index		84	84				
International Roughnes	ss Index (IRI)	N/A	N/A				
Lane & Width Informa	ation						
Number of Lanes		1	1				
Paved Width (ft)		11.1	11.1				
Lane Width (ft)		11.1	11.1				

ROUTE 0216: CAMPGROUND SITES 113-128 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pay	vement Cond	ition Rating (1	PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de		formulas	,		
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles):	0.21	Section Length (MI)	0.21				
Surface Type:	ASPHALT	Route Summary		•		•	
Roadway Condition In	formation						
Pavement Condition Ra	ating (PCR)	91	91				
Surface Condition Ratin	g (SCR)	91	91				
Roughness Condition In	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Ind	lex	100	100				
Transverse Cracking In	ndex	100	100				
Patching Index		98	98				
Rutting Index		91	91				
International Roughnes	ss Index (IRI)	N/A	N/A				
Lane & Width Informa	ition						
Number of Lanes		1	1				
Paved Width (ft)		10.6	10.6				
Lane Width (ft)		10.6	10.6				

ROUTE 0217: CAMPGROUND SITES 129-145 ACCESS

Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pa	vement Cond	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	finitions and f	ormulas			
Inspection Date: 1	/11/2017	Beginning Section MI	0				
Paved Length (Miles): 0	.22	Section Length (MI)	0.22				
Surface Type: A	SPHALT	Route Summary				•	
Roadway Condition Info	ormation						
Pavement Condition Ra	ting (PCR)	82	82				
Surface Condition Rating	(SCR)	82	82				
Roughness Condition Ind	ex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inde	ex	100	100				
Transverse Cracking Inc	lex	100	100				
Patching Index		97	97				
Rutting Index		82	82				
International Roughness	Index (IRI)	N/A	N/A				
Lane & Width Informat	ion						
Number of Lanes		1	1				
Paved Width (ft)		11.2	11.2				
Lane Width (ft)		11.2	11.2				

ROUTE 0218: CAMPGROUND SITES 146-158 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	ition Rating (I	PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for det	finitions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles):	0.23	Section Length (MI)	0.23				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition In	nformation						
Pavement Condition F	Rating (PCR)	87	87				
Surface Condition Ratio	ng (SCR)	87	87				
Roughness Condition In	ndex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index	K	100	100				
Alligator Crack Index		100	100				
Longitudinal Crack In	dex	100	100				
Transverse Cracking I	ndex	100	100				
Patching Index		100	100				
Rutting Index		87	87				
International Roughne	ess Index (IRI)	N/A	N/A				
Lane & Width Inform	ation						
Number of Lanes		1	1				
Paved Width (ft)		11.3	11.3				
Lane Width (ft)		11.3	11.3				

ROUTE 0219: CAMPGROUND SITES 159-174 ACCESS


Data Collection Vehicle (DCV) Rating



	Route Condition 1	Legend – Pavem	ent Condi	tion Rating (PCR)		
Poor (0 - 60)	Fair (61- 84)	Good (85		Excellent (9	_	Not Rat	ted
	See Ap	pendix for definit	ions and f	ormulas			
Inspection Date: 1/11/2017	Beginning	Section MP	0				
Paved Length (Miles): 0.23	Section L	ength (MI)	0.23				
Surface Type: ASPHAL	T Route Sur	nmary					
Roadway Condition Informatio	n						
Pavement Condition Rating (PC	R)	88	88				
Surface Condition Rating (SCR)		88	88				
Roughness Condition Index (RCI)]	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Index		100	100				
Transverse Cracking Index		100	100				
Patching Index		100	100				
Rutting Index		88	88				
International Roughness Index (IRI)	N/A	N/A				
Lane & Width Information							
Number of Lanes		1	1				
Paved Width (ft)		11.5	11.5				
Lane Width (ft)		11.5	11.5				

ROUTE 0220: CAMPGROUND SITES 175-191 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	ition Rating (PCR)		
Poor (0 - 6			(85 - 94)	Excellent (Not Ra	ted
		See Appendix for def	finitions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Mile	es): 0.25	Section Length (MI)	0.25				
Surface Type:	ASPHALT	Route Summary		•		•	
Roadway Condition	n Information						
Pavement Condition	on Rating (PCR)	91	91				
Surface Condition F	Rating (SCR)	91	91				
Roughness Condition	on Index (RCI)	N/A	N/A				
Distress Index Valu	ies						
Structural Crack In	ndex	100	100				
Alligator Crack Inc	dex	100	100				
Longitudinal Cracl	k Index	100	100				
Transverse Crackin	ng Index	100	100				
Patching Index		100	100				
Rutting Index		91	91				
International Roug	hness Index (IRI)	N/A	N/A				
Lane & Width Info	rmation						
Number of Lanes		1	1				
Paved Width (ft)		10.3	10.3				
Lane Width (ft)		10.3	10.3				

ROUTE 0221: CAMPGROUND SITES 192-208 ACCESS


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pay	ement Cond	ition Rating (I	PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
		See Appendix for de	finitions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles):	0.25	Section Length (MI)	0.25				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition In	formation						
Pavement Condition Ra	ating (PCR)	87	87				
Surface Condition Ratin	g (SCR)	87	87				
Roughness Condition In	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inc	lex	100	100				
Transverse Cracking In	ıdex	100	100				
Patching Index		100	100				
Rutting Index		87	87				
International Roughnes	ss Index (IRI)	N/A	N/A				
Lane & Width Informa	tion						
Number of Lanes		1	1				
Paved Width (ft)		11.3	11.3				
Lane Width (ft)		11.3	11.3				

ROUTE 0401: SPUR RESIDENCE ROAD WEST


Data Collection Vehicle (DCV) Rating



	Route (Condition Leg	end _ Pave	ement Condi	tion Rating (PCR)		
Poor (0 - 60)	Fair (6			85 - 94)	Excellent (Not Ra	ted
		*	· ·	initions and fo				
Inspection Date: 1/11/	2017	Beginning Se	ction MP	0				
Paved Length (Miles): 0.07		Section Leng	th (MI)	0.07				
Surface Type: ASP	HALT	Route Summ	ary					
Roadway Condition Inform	ation							
Pavement Condition Rating	(PCR)	89		89				
Surface Condition Rating (SC	CR)	89		89				
Roughness Condition Index (RCI)	N/A		N/A				
Distress Index Values								
Structural Crack Index		100		100				
Alligator Crack Index		100		100				
Longitudinal Crack Index		100		100				
Transverse Cracking Index		100		100				
Patching Index		100		100				
Rutting Index		89		89				
International Roughness Inc	lex (IRI)	N/A		N/A				
Lane & Width Information								
Number of Lanes		2		2				
Paved Width (ft)		14.8		14.8				
Lane Width (ft)		7.4		7.4				

ROUTE 0402: SPUR RESIDENCE ROAD EAST


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pay	ement Condi	ition Rating (1	PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (9		Not Ra	ted
, ,		See Appendix for de	,	ormulas	,		
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles): ().09	Section Length (MI)	0.09				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition Inf	formation						
Pavement Condition Ra	ating (PCR)	76	76				
Surface Condition Rating	g (SCR)	76	76				
Roughness Condition Inc	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Ind	ex	100	100				
Transverse Cracking In	dex	98	98				
Patching Index		99	99				
Rutting Index		76	76				
International Roughnes	s Index (IRI)	N/A	N/A				
Lane & Width Informa	tion						
Number of Lanes		2	2				
Paved Width (ft)		22.7	22.7				
Lane Width (ft)		13.3	13.3				

ROUTE 0403: CAMPGROUND HOUSING ROAD


Data Collection Vehicle (DCV) Rating



	Route (Condition Legend – Pav	ement Condi	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (Not Ra	ted
		See Appendix for de	finitions and f	ormulas			
Inspection Date:	1/11/2017	Beginning Section MP	0				
Paved Length (Miles): (0.05	Section Length (MI)	0.05				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition Inf	formation						
Pavement Condition Ra	ating (PCR)	67	67				
Surface Condition Rating	g (SCR)	67	67				
Roughness Condition Inc	dex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Ind	ex	100	100				
Transverse Cracking In	dex	100	100				
Patching Index		99	99				
Rutting Index		67	67				
International Roughnes	s Index (IRI)	N/A	N/A				
Lane & Width Informa	tion						
Number of Lanes		2	2				
Paved Width (ft)		15.7	15.7				
Lane Width (ft)		7.8	7.8				

ROUTE 0408: 100 K WATER TANK ROAD

Manual Rating



	Route (Condition Legend – Pav	ement Condi	ition Rating (PCR)		
Poor (0 - 60)	Fair (6		(85 - 94)	Excellent (Not Ra	ted
		See Appendix for def	initions and f	ormulas			
Inspection Date:	1/25/2016	Beginning Section MP	0.00				
Paved Length (Miles)	: 0.10	Section Length (MI)	0.10				
Surface Type:	ASPHALT	Route Summary					
Roadway Condition I	nformation						
Pavement Condition I	Rating (PCR)	53	53				
Surface Condition Rati	ing (SCR)	53	53				
Roughness Condition I	Index (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Inde	X	N/A	N/A				
Alligator Crack Index	ζ	73	73				
Longitudinal Crack Ir	ndex	53	53				
Transverse Cracking	Index	53	53				
Patching Index		73	73				
Rutting Index		90	90				
International Roughne	ess Index (IRI)	N/A	N/A				
Lane & Width Inform	nation						
Number of Lanes		1	1				
Paved Width (ft)		13	13				
Lane Width (ft)		13	13				

ROUTE 0408: 100 K WATER TANK ROAD

Condition Photos

Condition photos are shown only for manually rated roads. Use the PathView program to see images of DCV rated roads.



ORPI_0408_2987.JPG



ORPI_0408_2990.JPG



ORPI_0408_2994.JPG



ORPI_0408_2988.JPG




ORPI_0408_2992.JPG



ORPI_0408_2995.JPG

ROUTE 0409: GROUP CAMPGROUND ACCESS ROAD

Data Collection Vehicle (DCV) Rating



Route Condition Legend – Pavement Condition Rating (PCR)							
Poor (0 - 60)	Fair (6		1 (85 - 94)	Excellent (9		Not Ra	ted
. ,		See Appendix for d	, ,	formulas	,		
Inspection Date: 1	/11/2017	Beginning Section M	P 0				
Paved Length (Miles): 0	0.14	Section Length (MI)	0.14				
Surface Type:	ASPHALT	Route Summary				•	
Roadway Condition Inf	ormation						
Pavement Condition Ra	ting (PCR)	97	97				
Surface Condition Rating	g (SCR)	97	97				
Roughness Condition Inc	lex (RCI)	N/A	N/A				
Distress Index Values							
Structural Crack Index		100	100				
Alligator Crack Index		100	100				
Longitudinal Crack Inde	ex	100	100				
Transverse Cracking Inc	dex	100	100				
Patching Index		100	100				
Rutting Index		97	97				
International Roughness Index (IRI)		N/A	N/A				
Lane & Width Informat	tion						·
Number of Lanes		2	2				
Paved Width (ft)		21	21				
Lane Width (ft)		9.8	9.8				

Section 6 Paved Parking Area Condition Rating Sheets



Organ Pipe Cactus National Monument



ROUTE 0903: MAINTENANCE YARD

Manual Rating

FROM ROUTE 0205 (MAINTENANCE ACCESS ROAD)

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type	
1/26/2016	72690	NONPUBLIC	ASPHALT	
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation	
33,594	0.578	NOT APPLICABLE	NOT APPLICABLE	
Curb Type		Curb & Gutter Type		
NO CURB		NO CURB AND GUTTER		
Pavement Recommendation		Condition Rating / PCR		
PREVENTIVE MAINTENANCE		GOOD / 90		
Pouts Condition Logand Poyament Condition Poting (PCP)				

Route Condition Legend – Pavement Condition Rating (PCR)

Poor (0 - 60)

Fair (61-84)

Good (85 - 94)

Excellent (95 - 100)


Not Rated

See Appendix for definitions and formulas











ROUTE 0904A: VISITOR CENTER PARKING A

Manual Rating

FROM ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.07 ON RIGHT


TO ROUTE 0905 (OFFICE PARKING)

		Surface Type		
72424	PUBLIC	ASPHALT		
Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation		
0.624	5	DO NOTHING		
Curb Type		Curb & Gutter Type		
CONCRETE		NO CURB AND GUTTER		
Pavement Recommendation		Condition Rating / PCR		
IAINTENANCE	GOOD / 90			
Route Condition Legend – Pavement Condition Rating (PCR)				
Poor (0 - 60) Fair (61- 84) Good (85 - 94) Excellent (95 - 100) Not Rated See Appendix for definitions and formulas				
	Lane Miles (11' Widths) 0.624 Type RETE ommendation IAINTENANCE Route Condition Legend – Pav Fair (61-84) Good (Lane Miles (11' Widths) Curb Reveal (Inches) 0.624 5 Type Curb & G RETE NO CURB AT ommendation Condition R IAINTENANCE GOOD Route Condition Legend – Pavement Condition Rating (PCR)		










ROUTE 0904B: VISITOR CENTER PARKING B

Manual Rating

ADJACENT TO ROUTE 0010 (VISITOR CENTER DRIVE) AT MP 0.1 ON LEFT

Inspection Date	FMSS Number	User Access	Surface Type	
1/25/2016	105672	PUBLIC	ASPHALT	
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation	
8,145	0.14	5	DO NOTHING	
Curb Type		Curb & Gutter Type		
CONCRETE		NO CURB AND GUTTER		
Pavement Recommendation		Condition R	ating / PCR	
PREVENTIVE MAINTENANCE		GOOD / 90		
Route Condition Legend – Pavement Condition Rating (PCR)				
Poor (0 - 60)	, ,	(85 - 94) Excellent (95 - 10	0) Not Rated	
See Appendix for definitions and formulas				



ROUTE 0905: OFFICE PARKING

Manual Rating

FROM ROUTE 0904A (VISITOR CENTER PARKING A)

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type
1/25/2016	102991	NONPUBLIC	ASPHALT
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation
7,277	0.125	NOT APPLICABLE	NOT APPLICABLE
Curb Type		Curb & Gutter Type	
NO CURB		NO CURB AND GUTTER	
Pavement Recommendation		Condition Rating / PCR	
PREVENTIVE MAINTENANCE		GOOD / 90	

Route Condition Legend – Pavement Condition Rating (PCR)

Poor (0 - 60)

Fair (61- 84)

Good (85 - 94)

Excellent (95 - 100)

Not Rated


See Appendix for definitions and formulas



Note: Parking area consists of multiple surface types: 1 part Asphalt at 3,817 square feet; 1 part Concrete at 3,460 square feet.







ROUTE 0906: GROUP CAMPGROUND PARKING

Manual Rating

FROM END OF ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type
1/25/2016	102987	PUBLIC	ASPHALT
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation
12,611	0.217	NOT APPLICABLE	NOT APPLICABLE
Curb Type		Curb & Gutter Type	
NO CURB		NO CURB AND GUTTER	
Pavement Recommendation		Condition R	ating / PCR
HEAVY 3R TREATMENTS		POOR / 53	
Route Condition Legend – Payement Condition Rating (PCR)			

Poor (0 - 60)

Fair (61-84)

Good (85 - 94)

Excellent (95 - 100)


Not Rated

See Appendix for definitions and formulas










ROUTE 0907: CAMPGROUND PARKING

Manual Rating

ADJACENT TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.22 ON RIGHT

Inspection Date	FMSS Number	User Access	Surface Type		
1/25/2016	102774	PUBLIC	ASPHALT		
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation		
995	0.017	NOT APPLICABLE	NOT APPLICABLE		
Curb Type		Curb & Gutter Type			
NO C	NO CURB		NO CURB AND GUTTER		
Pavement Recommendation		Condition R	ating / PCR		
PREVENTIVE N	PREVENTIVE MAINTENANCE		GOOD / 90		
Route Condition Legend – Pavement Condition Rating (PCR)					
Poor (0 - 60)			0) Not Rated		





ROUTE 0908: DUMP STATION LOOP

Manual Rating

FROM ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.34 ON RIGHT


TO ROUTE 0200 (CAMPGROUND LOOP ROAD) AT MP 0.39 ON RIGHT

Inspection Date	FMSS Number	User Access	Surface Type		
1/25/2016	102436	PUBLIC	ASPHALT		
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation		
7,621	0.131	4	DO NOTHING		
Cur	Curb Type		Curb & Gutter Type		
CON	CONCRETE		NO CURB AND GUTTER		
Pavement Recommendation		Condition Rating / PCR			
PREVENTIVE	PREVENTIVE MAINTENANCE		GOOD / 90		
	Route Condition Legend – Pavement Condition Rating (PCR)				
Poor (0 - 60)	Fair (61- 84) Good	(85 - 94) Excellent (95 - 10	0) Not Rated		
See Appendix for definitions and formulas					













ROUTE 0909: CAMPGROUND HOUSING PARKING

Manual Rating

FROM END OF ROUTE 0403 (CAMPGROUND HOUSING ROAD)

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type
1/25/2016	102773	NONPUBLIC	ASPHALT
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation
2,638	0.045	NOT APPLICABLE	NOT APPLICABLE
Curb Type		Curb & Gutter Type	
NO (CURB	NO CURB AND GUTTER	
Pavement Recommendation		Condition Rating / PCR	
PREVENTIVE MAINTENANCE		GOOD / 90	
	D + C 1141 T 1 D	AC IIII DAI (DCD)	

Route Condition Legend – Pavement Condition Rating (PCR)

Poor (0 - 60)

Fair (61- 84)

Good (85 - 94)

Excellent (95 - 100)


Not Rated

See Appendix for definitions and formulas











ROUTE 0910: TILLOTSON PEAK WAYSIDE PARKING


Manual Rating

FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 14.67 ON LEFT

TO PARKING

FMSS Number	User Access	Surface Type		
109708	PUBLIC	ASPHALT		
Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation		
0.491	7	DO NOTHING		
Curb Type		Curb & Gutter Type		
CONCRETE		NO CURB AND GUTTER		
Pavement Recommendation		ating / PCR		
PREVENTIVE MAINTENANCE		GOOD / 90		
Route Condition Legend – Pavement Condition Rating (PCR)				
		0) Not Rated		
	109708 Lane Miles (11' Widths) 0.491 Type CRETE commendation MAINTENANCE Route Condition Legend – Pav Fair (61- 84) Good	109708 PUBLIC Lane Miles (11' Widths) Curb Reveal (Inches) 0.491 7 Type Curb & G CRETE NO CURB AN Commendation Condition R MAINTENANCE GOOD Route Condition Legend – Pavement Condition Rating (PCR)		





ROUTE 0911: AJO MOUNTAINS WAYSIDE PARKING

Manual Rating

FROM ROUTE 5000 (STATE HIGHWAY 85) AT MP 4.89 ON RIGHT

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type	
1/26/2016	109712	PUBLIC	ASPHALT	
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation	
30,415	0.524	7	DO NOTHING	
Curb Type		Curb & Gutter Type		
CONCRETE		NO CURB AND GUTTER		
Pavement Recommendation		Condition Rating / PCR		
PREVENTIVE MAINTENANCE		GOOD / 90		
Route Condition Legend – Pavement Condition Rating (PCR)				

Poor (0 - 60) Fair (61- 84)

Good (85 - 94)


Excellent (95 - 100)

Not Rated

See Appendix for definitions and formulas







ROUTE 0912: HOUSING AREA DUPLEX HOUSING PARKING

Manual Rating

FROM END OF ROUTE 0401 (SPUR RESIDENCE ROAD WEST)

TO PARKING

Inspection Date	FMSS Number	User Access	Surface Type
1/25/2016	115987	NONPUBLIC	ASPHALT
Area (Sq. Ft.)	Lane Miles (11' Widths)	Curb Reveal (Inches)	Curb Recommendation
1,747	0.03	NOT APPLICABLE	NOT APPLICABLE
Curb Type		Curb & Gutter Type	
NO CURB		NO CURB AND GUTTER	
Pavement Recommendation		Condition Rating / PCR	
PREVENTIVE MAINTENANCE		GOOD / 90	
	~		·

Route Condition Legend – Pavement Condition Rating (PCR)

Poor (0 - 60)

Fair (61- 84)

Good (85 - 94)

Excellent (95 - 100)


Not Rated

See Appendix for definitions and formulas









Section 7 Road Milepost Information



Organ Pipe Cactus National Monument



Road Milepost Information

This report section contains road milepost information for all paved roads in the park that were collected with the Data Collection Vehicle (DCV). The milepost data is obtained from the DCV by using a distance measuring instrument (DMI) that is calibrated to record mileage to the nearest thousandth of a mile. Park roads that were manually rated did not have milepost data collected, and thus are not included in this report section.

For Cycle 6, the information presented in this section differs from previous RIP cycles in that it does not contain the roadside features inventories for the paved park roads. Some examples of the features previously collected are signs, culverts/drop inlets, guardrails, curbing, pullouts, etc. If the park was collected in a previous RIP cycle, then the latest features data can be obtained by referencing the following:

Where to find the latest Features Inventories for NPS Parks:

- For Small Parks (parks with less than 10 miles of paved roads):
 - o Refer to Cycle 5 data (collected 2010 2014)
 - Features were reported in Section 9 of the *Cycle 5* RIP report
 - Video of features can be viewed using the PathViewVO program and Cycle 5 data
- For Large Parks (parks with more than 10 miles of paved roads):
 - o Refer to Cycle 4 data (collected 2006 2009)
 - Features were reported in Section 9 of the *Cycle 4* RIP report
 - Video of features can be viewed using the VisiData program and Cycle 4 data
 - O Note: Features inventories were updated in Large Parks in *Cycle 5* only on a route by route basis if the route was new or modified in *Cycle 5*. If this is the case for a particular route, then features for the route can be obtained using the *PathViewVO* program and *Cycle 5* data (same as above for Small parks).

Milepost Events Verified in Cycle 6

In Cycle 6, the following events were collected and reported in Section 7 of this report:

- Intersections with roads and parking areas
- All bridges and culverts with BIP Numbers (bridge inspection program numbers)
- Mile Marker Signs
- One-Way travel directions
- Overpasses
- Tunnels
- Low Water Crossings (LWCR)
- Surface type changes
- Construction areas where no pavement condition data was obtained

GPS Mileage Matching

A consistent survey milepost and constant route length as recorded by the Data Collection Vehicle (DCV) is a challenge to maintain from one collection cycle to the next. The challenge is due to many factors such as driver characteristics, DMI calibration, tire pressure etc. After Cycle 4 (~2010), a decision was made to hold constant the length of roads so long as there was no physical change from reconstruction projects or realignments that would result in a change to the length of a road. Consequently, the "GPS Mileage Match" was implemented to specify which cycle the route length is being matched. Route mileages and GPS are matched to a previous collection whenever there is no physical change to a route alignment. The route mileage and GPS is not matched to previous cycles whenever it is determined that a road length and GPS needs to be updated. When this happens the GPS and length is updated to the cycle that displays the change, and that collection cycle is used as the matching cycle in subsequent collections of the road. Thus, the Cycle 6 GIS could be either the survey length collected in Cycle 4, Cycle 5, or Cycle 6 and therefore, may not match the survey milepost displayed in the latest Cycle 6 DCV video which is viewable in *PathView VO*.

The features inventories and road logs collected on NPS routes contain mileposts that are determined from the corresponding cycle that the GPS is matched to. Therefore, the mileposts contained in the Cycle 4 or 5 features inventories or the Cycle 6 road logs may not exactly match the survey milepost collected in the latest Cycle 6 video of the road.

Locating Mile Marker Signs

For routes that have mile marker signs along them, the milepost reported by RIP will most likely not line up exactly with the sign located in the field. This could be happening for many reasons, most likely due to either the error falling within the acceptable calibration range of the vehicle, or the level of accuracy that the mile marker signs were placed in the field.

Because mile marker signs are important features in many project plans and location descriptions, RIP is reporting locations of mile marker signs in three ways in Cycle 6:

- 1. Mileposts from Cycle 6 GIS: the official RIP milepost taken from the features inventories and the matching GPS/mileage cycle as described above. This is the milepost that should be used on project plans and when finding locations in the field
- 2. Mileposts from Cycle 6 Video: milepost shown to help locate the mile marker sign in the latest *Path View VO* video.
- 3. Latitude / Longitude: a constant way of locating a mile marker sign so long as the park has not moved the sign

The mileposts from Cycle 6 Video and GIS should be nearly the same, but on longer roads it has been observed that the Video milepost deviates more from the official GIS milepost that comes from the matching cycle.

ROUTE 0010: VISITOR CENTER DRIVE

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 5000 (STATE HIGHWAY 85)
0.00	0.00	INTERSECTION	N/A	ROUTE 0011 (AJO MOUNTAIN DRIVE)
0.00	0.00	INTERSECTION	L	ROUTE 5000 (STATE HIGHWAY 85)
0.07	0.07	INTERSECTION	R	ROUTE 0904A (VISITOR CENTER PARKING A)
0.10	0.10	INTERSECTION	L	ROUTE 0904B (VISITOR CENTER PARKING B)
0.11	0.11	INTERSECTION	R	ROUTE 0904A (VISITOR CENTER PARKING A)
0.17	0.17	INTERSECTION	L	ROUTE 0101 (TWIN PEAKS ACCESS ROAD)
0.31	0.31	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.32	0.32	INTERSECTION	R	ROUTE 0012 (PUERTO BLANCO DRIVE)
0.34	0.34	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.34	0.34	INTERSECTION	R	ROUTE 0100 (RESIDENCE ACCESS ROAD)

ROUTE 0100: RESIDENCE ACCESS ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0010 (VISITOR CENTER DRIVE)
0.00	0.00	INTERSECTION	R	ROUTE 0010 (VISITOR CENTER DRIVE)
0.02	0.02	INTERSECTION	R	ROUTE 0010 (VISITOR CENTER DRIVE)
0.07	0.07	INTERSECTION	L	ROUTE 0205 (MAINTENANCE ACCESS ROAD)
0.17	0.17	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.37	0.37	INTERSECTION	R	UNPAVED ROUTE
0.53	0.53	INTERSECTION	R	ROUTE 0402 (SPUR RESIDENCE ROAD EAST)
0.83	0.83	INTERSECTION	R	UNPAVED SPUR
0.84	0.84	INTERSECTION	R	ROUTE 0408 (100 K WATER TANK ROAD)
1.08	1.08	INTERSECTION	L	ROUTE 0416 (VIP ROAD)
1.14	1.14	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
1.14	1.14	INTERSECTION	R	ROUTE 0100 (RESIDENCE ACCESS ROAD)

ROUTE 0101: TWIN PEAKS ACCESS ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0010 (VISITOR CENTER DRIVE)
0.00	0.00	INTERSECTION	L	ROUTE 0010 (VISITOR CENTER DRIVE)
0.23	0.23	INTERSECTION	L	ROUTE 0410 (DOMESTIC WATER WELLS ROAD)
0.51	0.52	LOW WATER CROSSING	N/A	HIGH WATER FLOW AREA
1.12	1.13	LOW WATER CROSSING	N/A	HIGH WATER FLOW AREA
1.32	1.32	INTERSECTION	N/A	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
1.32	1.32	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0200: CAMPGROUND LOOP ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.01	0.01	INTERSECTION	L	ROUTE 0206 (CAMPGROUND SITES 1-6 ACCESS)
0.04	0.04	INTERSECTION	L	ROUTE 0207 (CAMPGROUND SITES 7-15 ACCESS)
0.05	0.05	INTERSECTION	L	ROUTE 0208 (CAMPGROUND SITES 16-23 ACCESS)
0.07	0.07	INTERSECTION	L	ROUTE 0209 (CAMPGROUND SITES 24-34 ACCESS)
0.09	0.09	INTERSECTION	L	ROUTE 0210 (CAMPGROUND SITES 35-45 ACCESS)
0.10	0.10	INTERSECTION	L	ROUTE 0211 (CAMPGROUND SITES 46-57 ACCESS)
0.12	0.12	INTERSECTION	L	ROUTE 0212 (CAMPGROUND SITES 58-70 ACCESS)
0.13	0.13	INTERSECTION	L	ROUTE 0213 (CAMPGROUND SITES 71-85 ACCESS)
0.15	0.15	INTERSECTION	L	ROUTE 0214 (CAMPGROUND SITES 86-95 ACCESS)
0.16	0.16	INTERSECTION	L	ROUTE 0215 (CAMPGROUND SITES 96-112 ACCESS)
0.18	0.18	INTERSECTION	L	ROUTE 0216 (CAMPGROUND SITES 113-128 ACCESS)
0.20	0.20	INTERSECTION	L	ROUTE 0217 (CAMPGROUND SITES 129-145 ACCESS)
0.21	0.21	INTERSECTION	L	ROUTE 0218 (CAMPGROUND SITES 146-158 ACCESS)
0.22	0.22	INTERSECTION	R	ROUTE 0907 (CAMPGROUND PARKING)
0.23	0.23	INTERSECTION	L	ROUTE 0219 (CAMPGROUND SITES 159-174 ACCESS)
0.24	0.24	INTERSECTION	L	ROUTE 0220 (CAMPGROUND SITES 175-191 ACCESS)
0.25	0.25	INTERSECTION	L	ROUTE 0221 (CAMPGROUND SITES 192-208 ACCESS)
0.34	0.34	INTERSECTION	R	ROUTE 0908 (DUMP STATION LOOP)
0.39	0.39	INTERSECTION	R	ROUTE 0908 (DUMP STATION LOOP)
0.54	0.54	INTERSECTION	L	ROUTE 0221 (CAMPGROUND SITES 192-208 ACCESS)
0.57	0.57	INTERSECTION	L	ROUTE 0220 (CAMPGROUND SITES 175-191 ACCESS)
0.58	0.58	INTERSECTION	L	ROUTE 0219 (CAMPGROUND SITES 159-174 ACCESS)
0.59	0.59	INTERSECTION	L	ROUTE 0218 (CAMPGROUND SITES 146-158 ACCESS)
0.60	0.60	INTERSECTION	L	ROUTE 0217 (CAMPGROUND SITES 129-145 ACCESS)
0.62	0.62	INTERSECTION	L	ROUTE 0216 (CAMPGROUND SITES 113-128 ACCESS)
0.63	0.63	INTERSECTION	L	ROUTE 0215 (CAMPGROUND SITES 96-112 ACCESS)

ROUTE 0200: CAMPGROUND LOOP ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.64	0.64	INTERSECTION	L	ROUTE 0214 (CAMPGROUND SITES 86-95 ACCESS)
0.66	0.66	INTERSECTION	L	ROUTE 0213 (CAMPGROUND SITES 71-85 ACCESS)
0.67	0.67	INTERSECTION	L	ROUTE 0212 (CAMPGROUND SITES 58-70 ACCESS)
0.69	0.69	INTERSECTION	L	ROUTE 0211 (CAMPGROUND SITES 46-57 ACCESS)
0.70	0.70	INTERSECTION	L	ROUTE 0210 (CAMPGROUND SITES 35-45 ACCESS)
0.72	0.72	INTERSECTION	L	ROUTE 0209 (CAMPGROUND SITES 24-34 ACCESS)
0.73	0.73	INTERSECTION	L	ROUTE 0208 (CAMPGROUND SITES 16-23 ACCESS)
0.75	0.75	INTERSECTION	L	ROUTE 0207 (CAMPGROUND SITES 7-15 ACCESS)
0.76	0.76	INTERSECTION	L	ROUTE 0206 (CAMPGROUND SITES 1-6 ACCESS)
0.82	0.82	INTERSECTION	L	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
0.82	0.82	ONE-WAY END	N/A	N/A
0.82	0.82	INTERSECTION	R	ROUTE 0101 (TWIN PEAKS ACCESS ROAD)

ROUTE 0205: MAINTENANCE ACCESS ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.05	0.05	INTERSECTION	L	ROUTE 0915 (RESOURCE / LAW ENFORCEMENT PARKING)
0.08	0.08	INTERSECTION	N/A	ROUTE 0903 (MAINTENANCE YARD)

ROUTE 0206: CAMPGROUND SITES 1-6 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.09	0.09	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.09	0.09	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.09	0.09	ONE-WAY END	N/A	N/A

ROUTE 0207: CAMPGROUND SITES 7-15 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.12	0.12	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.12	0.12	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.12	0.12	ONE-WAY END	N/A	N/A

ROUTE 0208: CAMPGROUND SITES 16-23 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.13	0.13	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.13	0.13	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.13	0.13	ONE-WAY END	N/A	N/A

ROUTE 0209: CAMPGROUND SITES 24-34 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.15	0.15	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.15	0.15	ONE-WAY END	N/A	N/A
0.15	0.15	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0210: CAMPGROUND SITES 35-45 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.16	0.16	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.16	0.16	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.16	0.16	ONE-WAY END	N/A	N/A

ROUTE 0211: CAMPGROUND SITES 46-57 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.17	0.17	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.17	0.17	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.17	0.17	ONE-WAY END	N/A	N/A

ROUTE 0212: CAMPGROUND SITES 58-70 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.18	0.18	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.18	0.18	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.18	0.18	ONE-WAY END	N/A	N/A

ROUTE 0213: CAMPGROUND SITES 71-85 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.19	0.19	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.19	0.19	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.19	0.19	ONE-WAY END	N/A	N/A

ROUTE 0214: CAMPGROUND SITES 86-95 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.20	0.20	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.20	0.20	ONE-WAY END	N/A	N/A
0.20	0.20	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0215: CAMPGROUND SITES 96-112 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.21	0.21	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.21	0.21	ONE-WAY END	N/A	N/A
0.21	0.21	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0216: CAMPGROUND SITES 113-128 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.21	0.21	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.21	0.21	ONE-WAY END	N/A	N/A
0.21	0.21	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0217: CAMPGROUND SITES 129-145 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.22	0.22	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.22	0.22	ONE-WAY END	N/A	N/A
0.22	0.22	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)

ROUTE 0218: CAMPGROUND SITES 146-158 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	ONE-WAY END	N/A	N/A

ROUTE 0219: CAMPGROUND SITES 159-174 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.23	0.23	ONE-WAY END	N/A	N/A

ROUTE 0220: CAMPGROUND SITES 175-191 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.25	0.25	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.25	0.25	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.25	0.25	ONE-WAY END	N/A	N/A

ROUTE 0221: CAMPGROUND SITES 192-208 ACCESS

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	ONE-WAY START	N/A	N/A
0.25	0.25	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.25	0.25	INTERSECTION	R	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.25	0.25	ONE-WAY END	N/A	N/A

ROUTE 0401: SPUR RESIDENCE ROAD WEST

FROM MILEPO	TO OST MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	N/A	ROUTE 0402 (SPUR RESIDENCE ROAD EAST)
0.00	0.00	INTERSECTION	R	ROUTE 0402 (SPUR RESIDENCE ROAD EAST)
0.07	0.07	INTERSECTION	N/A	ROUTE 0912 (HOUSING AREA DUPLEX HOUSING PARKING)

ROUTE 0402: SPUR RESIDENCE ROAD EAST

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0100 (RESIDENCE ACCESS ROAD)
0.02	0.02	INTERSECTION	L	ROUTE 0401 (SPUR RESIDENCE ROAD WEST)
0.09	0.09	INTERSECTION	N/A	ROUTE 0402 (SPUR RESIDENCE ROAD EAST) UNPAVED SECTION

ROUTE 0403: CAMPGROUND HOUSING ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
0.00	0.00	INTERSECTION	R	ROUTE 0409 (GROUP CAMPGROUND ACCESS ROAD)
0.05	0.05	INTERSECTION	N/A	ROUTE 0909 (CAMPGROUND HOUSING PARKING)

ROUTE 0409: GROUP CAMPGROUND ACCESS ROAD

FROM MILEPOST	TO MILEPOST	FEATURE	SIDE	COMMENT
0.00	0.00	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.00	0.00	INTERSECTION	N/A	ROUTE 0101 (TWIN PEAKS ACCESS ROAD)
0.01	0.01	INTERSECTION	L	ROUTE 0200 (CAMPGROUND LOOP ROAD)
0.03	0.03	INTERSECTION	R	ROUTE 0403 (CAMPGROUND HOUSING ROAD)
0.14	0.14	INTERSECTION	N/A	ROUTE 0906 (GROUP CAMPGROUND PARKING)

Section 8 Appendix



Organ Pipe Cactus National Monument



Improvements to the RIP Index Equations and Determination of PCR

In 2005, the Federal Highway Administration (FHWA) began implementing the use of a Pavement Management System (PMS) to assist the National Park Service (NPS) in prioritizing Pavement Maintenance and Rehabilitation activities. The PMS used by FHWA is the Highway Pavement Management Application (HPMA) which has the ability to store inventory and condition data from the Road Inventory Program (RIP) and forecast future performance using prediction models. Outputs include performance and condition reports at the National, Region, Park, or Route level. A regional prioritized list and optimization have been produced for most regions and the Federal Highway Deferred Maintenance is calculated via the HPMA as well.

In an effort to improve the accuracy of treatment recommendations and pavement condition descriptions the distresses and indexes that comprise the Pavement Condition Rating (PCR), an extensive study was completed throughout 2010 that has resulted in changes to the RIP condition reporting method and specifically, the calculation of PCR. It was determined that a better representation of PCR could be achieved by modifying the relative impact certain distresses would have on the overall rating.

Through the use of HPMA data, it was noted that false failure indicators existed with the existing PCR model, and that it would be necessary to reduce their impact. The distresses affected in this way were Rutting and Roughness. Conversely, experience showed that roadways with extensive cracking present were often shown to have a high PCR. Therefore, the crack index models were adjusted to be more sensitive to changes in crack severity or quantity. It was also determined that these issues were not due to a problem with data acquisition (i.e. the RIP "van"), but with the way the collected data was processed. The final change was to provide guidance on when to use the Roughness Condition Index (RCI) in the PCR calculation. Roughness data is of little value to determining overall condition on routes that, due to their length or geometrics, have lower vehicle operating speeds. Therefore, in Cycle 5, only routes that have lengths of one half mile or greater and posted speed limits of 25 mph or greater will have RCI reported and included in the PCR calculations.

Additionally, methodologies were updated in 2013 for Manually Rated Routes (paved routes that the collection vehicle is unable to drive) as well as Parking Areas to provide more accurate condition data to the HPMA. These updated methodologies allow for the efficient assessment of pavement conditions using a visual inspection method to denote specific distresses. These distresses are indicative of current conditions, the causes for current and future deterioration, and identify the level of targeted repair and rehabilitation practices required.

The changes that were implemented were endorsed by management at both the FHWA and NPS. In order to show the effectiveness of these changes, several sites were ground truth tested in early 2014 to ensure that an improvement was achieved between the relationship of PCR and the actual Maintenance and Rehabilitation needs that were represented. The changes will allow greater use of RIP and HPMA data for not simply condition data reporting, but also as a reliable tool for project identification and selection.

Description of the Rating System

The Federal Highway Administration, National Park Service Road Inventory Program (NPS-RIP), collects roadway condition data on paved surfaces (asphalt, concrete, brick, and cobblestone) on roads, parkways, and parking areas in national parks nationwide. The road surface condition data is collected using an automated Data Collection Vehicle (DCV) and manually using Manually Rated Route (MRR) procedures. Roads having brick or cobblestone surfacing are not normally surveyed with the DCV, but are manually rated for condition rating.

The FHWA RIP is implemented based on the premise that an accurate pavement surface condition assessment can be accomplished using automated crack detection technology as applied to digital images. Various methods of pavement condition assessment have been developed over the years with varying degrees of accuracy and acceptance. The use of digital photography to record pavement images and subsequent crack detection and classification has undergone continuous improvements over the past decade. Digital cameras with increasingly superior resolution and high definition have become more affordable, and the proprietary programming code and algorithms have been improved in crack detection software.

With the use of quality digital photography and automated crack detection software, FHWA RIP is tasked with executing a pavement condition assessment on a network of roughly 5,700 miles of National Park Service roads and parkways. Because a subset of roads will be collected multiple times this cycle, the total collection length will be around 13,000 miles. Foremost in setting up the basis of pavement distress identification is employing the distress identification protocols used by FHWA. There is no single distress identification system that is universal among entities conducting a program of distress identification. For the purpose of the NPS RIP, FHWA employs distress identification protocols that are specific to this program.

FHWA has referenced the "Distress Identification Manual for the Long-Term Pavement Performance Program", Publication No. FHWA-RD 03-031, June 2003, as the point-of- reference for distress types on NPS pavement. In truth, the FHWA RIP distress types are similar to those described in the LTPP manual with some modifications. This document, "Distress Identification Manual for the NPS Road Inventory Program, Cycle 6, 2014-2020" was developed using the "Distress Identification Manual for the Long-Term Pavement Performance Program" as a guideline. Definitions of severity levels based on crack width contained in this document adhere to the LTPP Distress ID Manual. Modifications have been made to the definition of Alligator and Longitudinal Cracking and determination of Alligator Cracking severity. This manual also addresses Rutting and Roughness and its application to RIP.

Cycle 6 has launched in the spring of 2014 and will again comprise all parks, large and small, that are served by paved roads and/or parking areas. For Cycle 6, roughly 333 large and small parks will have all paved routes and parking areas collected at least once in the cycle, some will have multiple collections depending on the size of the park and the functional class of the route.

This "Distress Identification Manual for the NPS Road Inventory Program, Cycle 6, 2014-2020" will be used as a reference resource in crack detection and classification, determination of distress severity and extent, and in the calculation of distress index values for the FHWA RIP Cycle 6.


Explanation of the Condition Descriptions

In addition to the RIP Index changes that were implemented in Cycle 5, we will also aim to provide greater assistance in translating good/fair/poor categories into pavement needs categories. The PCR can be used to indicate the place in the Pavement Life Cycle and the types of treatments that should be considered now and into the future.

- Excellent/New: PCR of 95-100. Pavements in this range will require only spot repairs
- Good: PCR of 85-94. Pavements in this range will likely be candidates for preventive maintenance. Examples include Chip and Slurry Seals, Micro Surfacing and Thin Overlays.
- Fair: PCR of 61-84. Pavements in this range will likely be candidates of Light Rehabilitation (L3R). Examples include single-lift overlays up to 2.5 inches in total thickness, milling and overlays.
- Poor: PCR of 60 or below. Pavements in this range will likely be candidates of Heavy Rehabilitation or Reconstruction (H3R or 4R). Examples include Pulverization, Multiple Lift Overlays, and Reconstruction.

At this time, specific maintenance and rehabilitation activities should be evaluated and recommended at the project level. Site-specific conditions that influence treatment type should be determined based on performing a subsurface investigation and/or pavement condition survey, and not be based solely on RIP data. Additionally, RIP produces a snapshot of conditions the year in which the data was collected. For further information or to obtain additional PMS data from our (HPMA) please contact the Eastern Federal Lands pavement team.

Condition Categories and Treatments



Description of Pavement Treatment Types

- 1. **Preventive Maintenance** is a planned strategy of cost-effective treatments to an existing roadway system and its appurtenances that preserves the system, retards future deterioration, and maintains or improves the functional condition of the system (without significantly increasing the structural capacity). Preventive maintenance is typically applied to pavements in good condition having significant remaining service life. As a major component of pavement preservation, preventive maintenance is a strategy of extending the service life by applying cost-effective treatments to the surface or near-surface of structurally sound pavements. Examples of preventive treatments include asphalt crack sealing, chip sealing, slurry or micro-surfacing, thin and ultrathin hot-mix asphalt overlay, concrete joint sealing, diamond grinding, dowel-bar retrofit, and isolated, partial and/or full-depth concrete repairs to restore functionality of individual slabs.
- 2. Pavement Rehabilitation consists of structural enhancements that extend the service life of an existing pavement and/or improve its load carrying capacity. Rehabilitation techniques include restoration treatments and structural overlays. Rehabilitation projects extend the life of existing pavement structures either by restoring existing structural capacity through the elimination of age-related, environmental cracking of embrittled pavement surface or by increasing pavement thickness to strengthen existing pavement sections to accommodate existing or projected traffic loading conditions. Two sub-categories result from these distinctions, which are directly related to the restoration or increase of structural capacity.
 - **Light Rehabilitation (L3R)** Examples include single-lift overlays up to 2.5 inches in total thickness and milling and overlays for flexible pavements
 - **Heavy Rehabilitation (H3R)** Requires rehabilitation with grade improvement. H3R stands for resurfacing, restoration, and rehabilitation projects. H3R projects typically involve multi-depth (overlays greater than 2.5 inches) pavement improvement work (short of full-depth replacement) and targeted safety improvements. H3R projects generally involve retention of the existing three-dimensional alignment.
- 3. **Reconstruction** (4R) is defined as the replacement of the entire existing pavement structure by the placement of the equivalent or increased pavement structure. Reconstruction usually requires the complete removal and replacement of the existing pavement structure. Reconstruction may utilize either new or recycled materials incorporated into the materials used for the reconstruction of the complete pavement section. Reconstruction is required when a pavement has either failed or has become functionally obsolete.

Appendix A

Methodology for Determining Condition Ratings with the Data Collection Vehicle (DCV)

Surface Distresses Identified by the Data Collection Vehicle

<u>Surface Condition Rating – SCR</u>

Surface distresses are measured in the primary lane only. In the classification and measurement of all paved surface condition data, results will be reported in the database in record intervals of 0.02 miles (105.6 feet) (smallest granularity) along the route.

Surface distresses and rutting are determined from digital images that provide both the longitudinal and transverse profile. The images also provide an elevation profile of the road, creating a 3-dimensional image of the paved surface.

- Transverse Cracks
- Longitudinal Cracks
- Alligator Cracks
- Patching/Potholes
- Rutting

Each of the five surface distresses is assigned a computed surface distress index

- Transverse Crack Index
- Longitudinal Crack Index
- Alligator Crack Index
- Patching/Pothole Index
- Rutting Index

Surface distress data are classified as listed above, measured for severity, and quantified for extent. Classification, severity, and extent of these five surface distresses comprise the three main elements for calculation of Surface Condition Rating (SCR).

In addition to the five surface distresses, a Structural Crack Index is computed, which is a combination of the Longitudinal Crack Index and the Alligator Crack Index. The Structural Crack Index is then used in lieu of the LC and AC indices to compute SCR.

Roughness Condition Index - RCI

Additional condition data measured by DCV (lasers and accelerometers)

• Roughness (IRI)

Roughness is measured by FHWA's DCV and reported as International Roughness Index (IRI) in inches/mile. Using IRI, the Roughness Condition Index (RCI) is computed.

Pavement Condition Rating - PCR

Using the SCR (computed from the five surface distresses) and the RCI, an overall Pavement Condition Rating (PCR) is computed. The formula for PCR is:

Asphalt PCR =
$$(0.60 * SCR) + (0.40 * RCI)$$

Concrete PCR = RCI

A detailed description of each distress index formula, roughness index formula, SCR and PCR is provided in this document.

Each classified surface distress will fall into one or more severity - LOW, MEDIUM, or HIGH based on criteria listed. For each severity, an extent is established based on the measured quantity of the distress within that severity. Within each severity individual distresses are assigned a Maximum Allowable Extent (MAE). For example, LOW severity transverse cracking may be allowed up to 21.1 cracks within a 0.02 mile interval before it reaches MAE and fails.

The index formulas are based on a scale of 0 to 100. A PCR index value of 100 would indicate a "new" road with no measurable distresses or rough ride. A PCR value of 60 is determined to be terminable serviceability and the road is considered failed. The range of index values with condition descriptors is:

POOR = (less than or equal to 60), FAIR= (61 – 84), GOOD= (85 - 94), EXCELLENT= (95 - 100)

Index values are generally computed based on cumulative deducts of the measured severities. As shown in the index formulas below, as any single severity reaches or exceeds MAE, the index computes to a value of 60 or less, and the road fails for that 0.02 interval.

Note: As a result of a unique combination of measured surface distresses and IRI, index values occasionally compute to less than 0 or greater than 100. In this instance, an index value less than 0 defaults to 0. Index values greater than 100 defaults to 100. For all indices, a higher value indicates a better road condition, and a lower value indicates a poorer road condition.

On the following page, Table 1 summarizes the different types of distresses measured.

ASPHALT-SURFACED PAVEMENT DISTRESS TYPES WITH RUTTING AND ROUGHNESS					
Distress Type	Units Of Measure	Converted To	Defined Severity Levels?	Measured By	
Alligator Cracking	Square Feet	Percent of Lane Per 0.02 Mile	Yes	3 Dimensional pavement imaging system	
Transverse Cracking	Linear feet	Number of Cracks Per 0.02 Mile	Yes	3 Dimensional pavement imaging system	
Longitudinal Cracking	Linear feet	Percent of Lane Length Per 0.02 Mile	Yes	3 Dimensional pavement imaging system	
Patching / Potholes	Square Feet	Percent of Lane Per 0.02 Mile	No	3 Dimensional pavement imaging system	
Rutting	Inches	Rut Depth Per 0.02 Mile	Yes	3 Dimensional pavement imaging system	
Roughness	IRI	*RCI Per 0.02 Mile	No	DCV – Lasers / Accelerometers	

^{*}Note: Roughness is measured on concrete roadways, but surface distresses and rutting are not measured.

For concrete, PCR = RCI

Table 1. Distress summary

Alligator Cracking

Description:

Alligator cracking is considered a combination of fatigue and block cracking. It is a series of interconnected cracks in various stages of development. Alligator cracking develops into a many-sided pattern that resembles chicken wire or alligator skin. It can occur anywhere in the road lane. Alligator cracking must have a quantifiable area.

Severity Levels:

LOW

An area with little to no interconnecting cracks with no visible spalling. Cracks are less than or equal to a mean width of 0.25 in. (6mm). Cracks in the pattern are no further apart than 1 foot (0.328 m). May be sealed cracks with sealant in good condition and a crack width that cannot be determined.

MEDIUM

An area of interconnected cracks that form a complete pattern. Cracks may be slightly spalled. Cracks are greater than 0.25 in. (6 mm) but less than or equal to 0.75 in. (19 mm) or any crack with a mean width less than or equal to 0.75 in. (19 mm) and adjacent low severity cracking. Cracks in the pattern are no further apart than 6 in. (150 mm).

HIGH

An area of interconnected cracks forming a complete pattern. Cracks are moderately or severely spalled. Cracks are greater than 0.75 in. (19mm) or any crack with a mean width less than or equal to 0.75 in. (19mm) and adjacent medium to high severity random cracking.

A combination of observed crack width and crack pattern is used to determine overall severity of alligator cracking. Based on above description of each severity, the highest level of crack width and crack pattern determines overall severity as shown in Table 2.

ALLIGATOR CRACKING SEVERITY LEVELS					
	CRACK	CRACK PATTERN			
	SEVERITY	LOW	MED	HIGH	
CD A CIZ	LOW	LOW	MED	HIGH	
CRACK WIDTH	MED	MED	MED	HIGH	
WIDIII	HIGH	HIGH	HIGH	HIGH	

Table 2. Alligator Crack Severity Levels

Longitudinal Cracking

Description:

Longitudinal cracking occurs predominantly parallel to the pavement centerline. It can occur anywhere within the lane. Longitudinal cracks occurring in the wheelpath may be noteworthy.

Severity Levels:

LOW

Cracks with a mean width less than or equal to 0.25 in. (6 mm). This also includes sealed cracks with sealant in good condition and a width that cannot be determined.

MEDIUM

Cracks with a mean width greater than 0.25 in. (6 mm) but less than 0.75 in. (19 mm). Also, any crack with a mean width less than 0.75 in. (19 mm) and adjacent random low severity cracking.

HIGH

Cracks with a mean width greater than 0.75 in. (19 mm). Also, any crack with a mean width less than 0.75 in. (19 mm) and adjacent random medium to high severity cracking.

Transverse Cracking

Description:

Transverse cracking occurs predominantly perpendicular to the pavement centerline. It can occur anywhere within the lane.

Severity Levels:

LOW

Cracks with a mean width of less than or equal to 0.25 in. (6 mm). Sealed cracks with sealant in good condition and a width that cannot be determined.

MEDIUM

Cracks with a mean width greater 0.25 in. (6 mm) and less than or equal to 0.75 in. (19 mm). Also, any crack with a mean width less than 0.75 in. (19 mm) and adjacent random low severity cracking.

HIGH

Cracks with a mean width greater than 0.75 in. (19 mm). Also, any crack with a mean width less than 0.75 in. (19 mm) and adjacent random medium to high severity cracking.

Patching and Potholes

Description:

Patching is an area of pavement surface that has been removed and replaced with patching material or an area of pavement surface that has had additional patching material applied. Patching may encompass partial lane or full lane width. On full lane width patching; the total, contiguous length of patch may not exceed 0.100 mi. (0.161 km). (Any full-lane patch exceeding 0.100 mi. in length is considered a pavement change). Patching must have a quantifiable area.

Potholes are bowl-shaped holes of various sizes occurring in the pavement surface.

Manhole covers should not be rated as patches unless there is obvious patching around the manhole.

Speed bumps should not be rated as patches

Severity Levels:

There are no stratified severities for Patching and Potholes. They either are present or they are not.

RUTTING

Description:

Rutting is a longitudinal surface depression in the wheelpath.

Severity Levels:

LOW

Ruts with a measured depth of 0.20 inches to 0.49 inches Ruts less than 0.20 in. are not included in the distress calculations.

MEDIUM

Ruts with a measured depth of 0.50 inches to 0.99 inches

HIGH

Ruts with a measured depth greater than 1.00 inch

ROUGHNESS

Description:

Roughness is the measurement of the unevenness of the pavement in the direction of travel. It is measured in units of IRI (International Roughness Index), inches per mile, and is indicative of ride comfort.

Severity Levels:

There are no stratified severity levels for roughness. The roughness (or smoothness) of a road surface can be defined by IRI in the following table.

IRI DESCRIPTIONS				
Type of Road	Typical IRI (in/mile)			
New Road, no noticeable roughness	<90			
Small level of roughness	90 – 126			
Road of average roughness	126 – 190			
Road with above average roughness	190 – 253			
Road with severe roughness	253 – 380			
Nearly impassable	>380			

Table 3. International Roughness Index

Roughness Collection Parameters

On shorter roads with a lower speed limit the usefulness in collecting and reporting IRI is negligible. Lower, inconsistent speeds can lead to a less accurate IRI value. Therefore RIP has put in place the following protocols for reporting IRI.

International Roughness Index (IRI) is not reported on routes with the following criteria:

- Posted speed limit is less than 25 mph
- Length of route is less than 0.50 miles

When a collected route has a posted speed limit of at least 25 mph and length of at least 0.50 miles, IRI will be collected except on road sections where the speed is less than 20 mph

Other situations may arise where the speed and length factors are met, but reporting IRI could lead to an inaccurate PCR. RIP will determine whether or not it is reasonable to report IRI on these routes on a case by case basis.

Index Formulas

Note: All index formulas listed below contain MAE applicable to 0.02 mile (105.6 feet) interval.

Alligator Crack Index

```
AC INDEX = 100 - 40 * [(\%LOW / 35) + (\%MED / 15) + (\%HI / 5)]
```

Where:

The values %LOW, %MED and %HI report the percentage of the observed pavement (0.02 mile, primary lane) that contains alligator cracking within the respective severities. These values range from 0 to 100.

%LOW = Percent of total area (primary lane, 0.02 in length), low severity %MED = Percent of total area (primary lane, 0.02 in length), medium severity %HI = Percent of total area (primary lane, 0.02 in length), high severity

Percent of total area is computed as:

square foot area of alligator crack severity (0.02 mile)*(lane width)

In AC_INDEX, the denominators 35, 15, and 5 are the Maximum Allowable Extents (MAE) for each severity. In other words, we will allow up to 35% of low severity alligator cracking for a 0.02 interval before failure, 15% for medium severity, and so on. As you can see, if any single severity reaches MAE the resulting index value is 60, or failure.

Longitudinal Crack Index

$$LC_{INDEX} = 100 - 40 * [(\%LOW / 175) + (\%MED / 75) + (\%HI / 25)]$$

Where:

The values %LOW, %MED, and %HI report the length of longitudinal cracking within each severity as a percent of the section length (0.02 mile, primary lane). These values are greater than or equal to 0 and can exceed 100.

%LOW = Percent of interval length (primary lane, 0.02 in length), low severity %MED = Percent of interval length (primary lane, 0.02 in length), medium severity %HI = Percent of interval length (primary lane, 0.02 in length), high severity

Percent of interval length is computed as:

length of respective longitudinal cracking (0.02 mile)*(105.6 ft.)

In LC_INDEX, the denominators 175, 75, and 25 are the Maximum Allowable Extents (MAE) for each severity. In other words, we will allow up to 175% of low severity longitudinal cracking for a 0.02 interval before failure, 75% for medium severity, and so on. As you can see, if any single severity reaches MAE the resulting index value is 60, or failure.

Structural Crack Index

$$SC_{INDEX} = [100 - ((100 - AC_{INDEX}) + (100 - LC_{INDEX}))]$$

Structural Crack Index is a combination of Alligator Cracking and Longitudinal Cracking, and is used in the SCR formula in lieu of AC and LC separately.

Transverse Crack Index

$$TC_{INDEX} = 100 - 40 * [(LOW / 21.1) + (MED / 4.4) + (HI / 2.6)]$$

Where:

The values LOW, MED and HI report a count of the total number of transverse cracks (reported to three decimals) within each severity level, where one transverse crack is equal to the lane width. These values are greater than or equal to 0.

LOW = Number of cracks in interval (primary lane, 0.02 in length), low severity MED = Number of cracks in interval (primary lane, 0.02 in length), medium severity HI = Number of cracks in interval (primary lane, 0.02 in length), high severity

Number of cracks is computed as:

Total length of transverse cracks
Lane width

In TC_INDEX, the denominators 21.1, 4.4, and 2.6 are the Maximum Allowable Extents (MAE) for each severity. In other words, we will allow up to 21.1 low severity transverse cracks for a 0.02 interval before failure, 4.4 cracks for medium severity, and so on. As you can see, if any single severity reaches MAE the resulting index value is 60, or failure.

Patching Index

PATCH_INDEX =
$$(100 - 40) * (\% PATCHING / 80)$$

Where:

The value %PATCHING reports the percentage of the observed pavement (0.02 mile, primary lane) that contains patching/potholes. This value ranges from 0 to 100.

%PATCHING = Percent of total area (primary lane, 0.02 in length)

Percent of total area is computed as:

square foot area of patching/potholes (0.02 mile)*(lane width)

There are no severity levels for patching. It either exists or does not.

There are no severity levels for patching. It either exists or does not. In PATCH_INDEX, the denominator 80 is the Maximum Allowable Extent (MAE) for each severity. In other words, we will allow up to 80% patching for a 0.02 interval before failure. As you can see, if patching/potholes reaches MAE the resulting index value is 60, or failure.

Rutting Index

RUT_INDEX =
$$100 - 40 * [(\%LOW / 535) + (\%MED / 205) + (\%HI / 40)]$$

Where:

20 rut depth measurements are taken per 0.02 interval for each of 2 wheel paths (left and right), resulting in a total of 40 measurements taken for both wheel paths. Each wheelpath is analyzed independently for rut severities. The values %LOW, %MED and %HI report the percentage of the 40 measurements within that severity. These values range from 0 to 200.

%LOW = Percent of LOW ruts in left wheelpath based on 20 ruts, plus percent of LOW ruts in right wheelpath based on 20 ruts.

%MED = Percent of MED ruts in left wheelpath based on 20 ruts, plus percent of MED ruts in right wheelpath based on 20 ruts.

%HI = Percent of HI ruts in left wheelpath based on 20 ruts, plus percent of HI ruts in right wheel path based on 20 ruts.

Percent of rut measurements within each severity can also be computed as:

$$\frac{(total\ number\ of\ ruts\ within\ each\ severity\ in\ both\ wheelpaths)}{20} \times 100$$

In RUT_INDEX, the denominators 535, 205, and 40 are the Maximum Allowable Extents for each severity; Low, Medium, and High, respectively. Only the MAE for high severity rutting can fail a section, since 200% of *only* low severity ruts would yield a rut index of 85 and 200% of *only* medium severity ruts would yield a rut index of 61.

Roughness Condition Index (Asphalt)

$$RCI = 32 * [5 * (2.718282^{(-.0041 * AVG IRI)})]$$

Where:

The value AVG IRI reports the average value of the Left IRI and Right IRI measurements for the interval (0.02 mile, primary lane). This value can range from approximately 40 to 999.0.

Average IRI is computed as:

There is no applicable threshold for failure for this index.

Roughness Condition Index (Concrete)

$$RCI = (-0.0012)(IRI^2) + (0.0499)(IRI) + 99.542$$

For concrete, PCR = RCI

Surface Condition Rating Index

SCR = Lowest Index Value Of: [SC_INDEX, TC_INDEX, PATCH_INDEX, RUT_INDEX]

Note: The modified SCR equation above combines AC_INDEX and LC_INDEX, and considers that a single AC/LC index value of the Structural Crack Index (SC_INDEX). The lowest of the four computed index values (SC_INDEX, TC_INDEX, PATCH_INDEX, or RUT_INDEX) becomes the SCR.

Where:

See above for determinations of SC_INDEX, TC_INDEX, PATCH_INDEX and RUT_INDEX.

The threshold for failure for this index is SCR = 60.Data Collection Vehicle Subsystems

Data on paved roads is collected by FHWA using a Pathway Services Inc. Data Collection Vehicle (DCV), called a PathRunner. The DCV is driven in the primary-direction lane at posted speed limits and less.

Cameras

Forward-facing and rear-facing video is collected as jpeg digital imagery files at a frequency of every 26.4feet.

Two forward-facing cameras are mounted above the vehicle cab, one pointed straight ahead and the other to the right shoulder providing seamless roughly 120 degree viewing. A third camera is mounted in the rear of the vehicle, recording the left shoulder.

CAMERA SPECIFICATIONS TWO FORWARD / ONE REAR FACING CAMERA		
Camera lens/type	Prosilica GT 2750 (GigE Technology)	
Image format	*.jpg	
Image resolution	2750 x 2200, 18 frames/second	
Image pixel size	depends on distance	
Zoom ratio	16mm Fixed	
	Aperture Range F 1.8 – Infinity (P-Iris,	
Iris range	Automatic	

Pavement Imaging and Rutting

High resolution rutting data and surface imaging are collected in a single data stream using a three-dimensional (3D) pavement surface transverse profile data acquisition system. The 3D camera captures a laser line as it is projected over the pavement surface and uses the location of this line to measure the height deviations of the pavement surface. These height deviations can be used to calculate rutting in both wheelpaths. These deviations also provide a grayscale image detailing the change in height throughout the surface, i.e. providing depth measurements for cracking.

THREE-DIMENSIONAL PAVEMENT SURFACE AND TRANSVERSE PROFILE DATA ACQUISITION SYSTEM		
Surface Image Specifications		
Image size	1536 pixels/scan @3000 Hz	
Image width	4 meters (3950 mm nominal)	
Laser class	3B	
Power	16W (Two lasers @ 8W Ea)	
Vehicle speed limitations	62 mph	
Environment	Dry pavement, day or night	
Sensor size (approximate)	1536 pixels x 512 pixels	
Image display length	26.4 feet	
Rutting Specifications		
Reported rut depth units	Inches	
Vehicle speed limitations	Up to 62 mph	
Sampling rate	3000 profiles/second	
Transverse resolution	1536 points/profile	
Transverse field-of-view	14 feet	
Depth accuracy (nominal)	<1mm	
Environment	Dry pavement, day or night, above 32 degrees F	
Adherence to specifications	ASTM E1703M-95 (reapproved 2005)	

Distance Measuring Instrument (DMI)

The DMI (Distance Measuring Instrument) obtains road length measurements that are accurate to 0.15% for speeds up to 60 mph. The DMI is connected to the hub of the rear wheel on the driver's side, and is calibrated to the revolutions of the rear vehicle axle on a regular basis.

Roughness (IRI)

IRI SPECIFICATIONS	
Reported IRI units	Inches/mile
Vehicle speed limitations	12-62 mph
IRI equipment certification	Texas Transportation Institute (TTI)
Wavelengths accommodated	0.5 feet to 300 feet
IRI computed & reported	World Bank Technical Paper Number 46
Environment	Dry pavement, day or night, above 32 degrees
Adherence to specifications	ASTM E950 Class 1 & AASHTO M 328

The collection system includes a South Dakota type laser profiler manufactured based on active Class 1 ASTM E950 standards. The dynamic profile of the pavement surface is collected from which the IRI roughness data is computed. The sensors include one accelerometer on each wheelpath, one height sensor (laser) on each wheelpath, and a distance transducer.

GPS & Inertial Systems

GPS is collected by an onboard system employing Omnistar real time correction and a spinning gyroscope to provide accurate positioning data in instances of satellite obstruction. All GPS coordinates are tied to an image and linear distance measurements.

GPS SPECIFICATIONS		
Static accuracy	Sub-meter	
Dynamic accuracy	2-3 meters	
Receiver	12 satellite tracking	
Coordinate system	Lat Lon WGS 84	
Environment	Day or night	
Cross-slope	± 1.75%	
Grade	± 1.75%	
Adherence to specifications	ASTM E1703M-95 (reapproved 2005)	

*NOTE – GPS accuracy is dependent on many different factors. Satellite constellation, tree coverage, GPS receiver quality, and real-time correction availability can all affect the locational and elevation accuracies. The elevation (z coordinate) accuracy is less dependable than locational or horizontal accuracy (x/y coordinates or latitude/longitude). In areas of heavy tree coverage or poor satellite constellations, elevation data can vary by as much as +/- 100 feet.

Appendix B

Methodology for Determining Condition Ratings Using Manual Rating Procedures

Description of Manual Rating Methods

In 2013, the Federal Highway Administration updated existing Manual Rating Procedures in an effort to better align pavement conditions for Manually Rated Routes and Parking with the Highway Pavement Management Application (HPMA). HPMA is the Pavement Management System used by the FHWA to store inventory and condition data from the Road Inventory Program (RIP) and forecast future performance using prediction models. HPMA uses pavement condition data (collected by the Road Inventory Program) to develop life cycles for pavements and recommend treatments to maximize useable pavement life while minimizing costs associated with maintenance and repair.

The Federal Highway Administration (FHWA) developed a set of manual rating methods for pavement that are appropriate for Federal Roadways. Two different methods were developed for linear roads and a separate method was developed for parking areas and nonlinear roads. These methods employ a 0 to 100 rating scale and improve consistency and objectivity in the manual evaluation of surface distresses. They are compatible with ratings that are collected by the automated Data Collection Vehicle (DCV).

- The first of the two manual evaluation methods for roads uses rating criteria to assign index values to each distress type based on a visual evaluation of severity and extent.
- The second manual evaluation method for roads is very time demanding and is best employed on only a select set of routes which may have the highest visitor use and require a more intensive assessment. This method will be used for the Manual Rating of Function Class 1, 2, 7, and 8 Roads. This method is based on measurements that are recorded for each instance of a surface distress. These measurements are converted into index values using conversion formulas.
- Parking areas and non-linear roads are rated similar to the first method shown above, however, there are some slight differences due to the non-linear nature.

The details and criteria used for each of these rating methods are outlined below.

Visual Inspection Method for Manually Rating Secondary Roads

The visual inspection method for manually rated roads uses condition rating criteria that have been developed by FHWA. This criteria is based on a visual evaluation of the severity and extent of distresses to determine the overall condition of the roadway. This method is used for secondary roads that are Functional Class 3, 4, 5, and 6. This constitutes the majority of manually rated roads collected by the Road Inventory Program.

Rating Section Lengths

For this method, Manually Rated Roads are rated in sections. These sections may be made based on length of changes in surface type or condition as described below. The ratings are then aggregated to give an overall rating for the Route:

- Rating sections should be no longer than 0.25 miles in order to keep the area being rated manageable.
- A new rating section may be started based on changes in condition, width, or surface type if these changes represent a significant portion of the route (are not isolated instances).
- If the road condition, width, and surface type remain constant then new sections do not need to be created unless the road exceeds 0.25 miles.

Rating Criteria

For this method, Manually Rated Roads are evaluated using a visual inspection of the six distress types listed below. Each distress is assigned one of five index values. An overall Surface Condition Rating (SCR) and Pavement Condition Rating (PCR) are calculated based on these index values.

- Alligator Cracking
 - o Rating based on percentage of road surface affected
- Longitudinal Cracking
 - o Rating based on severity level (crack width) and percentage of road section length of longitudinal cracks
- Transverse Cracking
 - o Rating based on crack width, crack spacing, and percentage of surface affected
- Patching
 - o Rating based on percentage of road surface affected
- Rutting
 - o Rating based on percentage of road section length affected by visible rutting (>1 inch depth) that requires remediation
- Roughness
 - o Manual assessments of roughness are not made due to the subjectivity of the measurement. Therefore, roughness is not incorporated into the PCR calculation of manually rated roads.

Concrete Routes also receive a PCR rating based on visual evaluation of the following six distress types.

- Slab Faulting at Joints
- Slab Cracking and breakup
- Surface Delamination and Pop-outs
- Joint Distresses
- Patching

Distress Measurement Method for Manually Rating Primary Roads

A more intensive and time demanding assessment than our standard method was developed for Primary roads that are functional class 1, 2, 7, or 8. These high visitation roads are usually accessible by the automated Data Collection Vehicle but in rare instances may need to be manually rated. The method developed is based on measuring each instance of a distress. These measurements are totaled over each section length being measured and are then converted into index values between 0 and 100 (100 being a road with no distress) using index formula equations outlined below. The goal of this method is to produce measured index values which are directly comparable to the automated DCV.

Rating Section Lengths

For the distress measurement method roads are broken into sections in order to rate. Distress measurements are totaled for each section separately in order to determine the index value for that particular section. The section length to be rated is determined based on the following rules:

- Rating sections are between 0.25 and 0.50 miles long
- A new rating section is created if there is a significant change in condition or pavement width
- If there are no significant changes in condition or pavement width, rating sections are broken at equal intervals, typically 0.50 miles

Manual Distress Measurements

Alligator Cracking

- Alligator cracking is measured by area (square feet). Instances of Alligator cracking are measured along the length and multiplied by the average width of the distressed area.
- The index for alligator cracking takes the total area of cracking compared to the interval length and converts it to a percentage. That percentage is then input into an index formula that yields a value between 0 and 100 (0 being the most distressed).
- Severity levels are not defined for manually measured Alligator cracks. The Alligator Crack Index formula is calculated based on an assumption of medium severity.

Longitudinal Cracking

- Longitudinal cracking (cracking in the direction parallel to the roadway) is measured by length (ft.).
- The index for longitudinal cracking takes the total length of cracking compared to the interval length and converts it to a percentage broken down by severity. That percentage is then input into a formula that yields a value between 0 and 100 (0 being the most distressed).
- Two severity levels are defined for manually measured Longitudinal Cracks. Lower severity cracks are those with a mean width of less than 0.25 inches. Sealed cracks with sealant in good condition are also considered lower severity. Higher severity cracks are those with a mean width of greater than 0.25 inches.

Transverse Cracking

- Transverse cracking (cracking in the direction perpendicular to the roadway) is measured by length (ft).
- The index for transverse cracking takes the total number of cracks (1 crack would encompass the full lane) broken down by severity. The total numbers of each severity are then put into a formula that yields a value between 0 and 100 (0 being the most distressed).
- Two severity levels are defined for manually measured Transverse Cracks. Lower severity cracks are those with a mean width of less than or equal to 0.25 inches. Sealed cracks with sealant in

good condition are also considered lower severity. Higher severity cracks are those with a mean width of greater than 0.25 inches.

Patching and Potholes

- Patching and Potholes are measured by area (square feet). Instances of Patching are measured along the length and multiplied by the average width of the patch.
- Instances of full lane width patching cannot be longer than 0.100 miles, otherwise is should be considered a pavement change rather than a distress.
- There are no stratified severities for Patching. It is either present or it is not.

Rutting

- Visible rutting is measured by length (ft.) in each wheel path. Only visible ruts are rated, which are ruts greater than 1 inch deep.
- All rutting recorded in a manual rating is considered to be high severity (> 1 inch). Lesser severities are generally not distinguishable in a visual inspection.

Roughness

• Manual assessments of roughness are not made due to the subjectivity of the measurement. Therefore, roughness is not incorporated into the PCR calculation of manually rated roads.

Index Formulas for Distress Measurement Method:

The method used to convert distress measurements into index values is shown below. The Surface Condition Rating and Pavement Condition Rating are calculated based on these index values.

Alligator Crack Index for Manual Rating:

AC INDEX =
$$100 - 40 * (\% ALLIGATOR / 15)$$

Where:

% ALLIGATOR = Percent of total area of section being rated that contains Alligator cracking.

Longitudinal Crack Index for Manual Rating:

$$LC_{INDEX} = 100 - 40 * [(\%LOW / 175) + (\%MED / 75)]$$

Where:

%LOW = Percent length of longitudinal cracks where crack width less than or equal to 0.25 inches

%HIGH = Percent length of longitudinal cracks where crack width greater than 0.25 inches

Transverse Crack Index for Manual Rating:

$$TC_{INDEX} = (100 - 40) * [(LOW / 21.1) + (MED / 4.4)]$$

Where:

LOW = Count of the total number of transverse cracks within the section length where one transverse crack is equal to the lane width and the crack width ≤ 0.25 inches HIGH = Count of the total number of transverse cracks within the section length where one transverse crack is equal to the lane width and the crack width ≥ 0.25 inches

Number of cracks is computed as:

Total length of transverse cracks/Lane width

Patching Index for Manual Rating:

Where:

%PATCHING = Percentage of pavement section that contains patching/potholes.

Rutting Index for Manual Rating:

$$RUT_INDEX = 100 - 40 * (\% RUTTING / 40)$$

Where:

%RUTTING = Percentage length of high severity rutting within the section being measured.

Method for Manually Rating Paved Parking Areas and Non-Linear Roads

Parking areas are evaluated based on a visual inspection using condition rating criteria that has been developed by FHWA. This criteria is based on a visual evaluation of the severity and extent of distresses to determine the overall condition of the parking area. This overall condition rating is linked to the level of repair and rehabilitation practices required.

A distress index is determined for each of the distresses listed below for Asphalt and Concrete Parking areas. The overall Pavement Condition Rating (PCR) of the parking lot is driven by the most severe distress present.

Rating Criteria:

Asphalt Parking Distress Types

- Alligator Cracking
 - o Rating based on percentage of road surface affected
- Longitudinal, Transverse and Block cracking
 - o Rating based on crack width, crack spacing, and percentage of surface affected
- Rutting and Distortions
 - o Rating based on percentage of road surface affected
- Hot Mix Asphalt Patches
 - o Rating based on overall percentage of HMA patches
- Potholes and Cold Patches
 - o Rating based on percentage of road surface affected
- Surface Raveling and Bleeding
 - o Rating based on percentage of road surface affected

Concrete Parking Distress Types

- Slab Faulting at Joints
 - o Rating based on height differential between adjacent slabs or pieces of broken slabs
- Slab Cracking and breakup
 - o Rating based on quantity of cracks and if slab is acting to able distribute load as designed
- Surface Delamination and Pop-outs
 - o Rating based on percentage of road surface affected to include pop-outs, spalls and surface delamination
- Joint Distresses
 - o Rating based on sealant condition and concrete distresses at/or adjacent to joints
- Patching
 - o Rating based on percentage of road surface affected

Curb Inspection and Treatments

During inspections of manually rated parking lots and routes, the curb reveal and overall curb condition are evaluated. The curb condition is used to determine a recommendation.

Curb Reveal

The vertical distance on the curb face from the gutter flow line or pavement surface to the top of curb. When resurfacing adjacent to curb, the resulting curb reveal should be no less than 4 inches. Additionally, when resurfacing adjacent to a gutter, the resulting pavement surface should be flush with the gutter pan. In cases where a resurfacing would violate either of these parameters, the surface may need to be milled or removed to adjust to these field conditions.

Curb Recommendations

The following treatment categories are based on the overall percentage of distresses along the entire curb structure for a specific pavement structure. Distresses include spalling, cracking, loss of material and any other damage which prevents the curb from conveying storm runoff or failing to perform in its intended function.

- Overall curb damage ranging 0%-5%:
 - o DO NOTHING
- Overall curb damage ranging 5%-20%
 - o LIGHT REPAIR
- Overall curb damage ranging 20%-50%
 - o MODERATE REPAIR
- Overall curb damage greater than 50%:
 - o REPLACE

GPS for Manually Rated Roads and Parking

GPS information for Manually Collected Cycle 6 Routes will be recorded using the latest hardware and software by TRIMBLE 6000 Series GeoXT. Cycle 6 GPS collection units will allow access to GPS and GLONASS, improving overall GPS reliability, accuracy and precision to submeter accuracy. Additionally, the new GPS units have an enhanced ability to collect accurate signals underneath tree cover or adjacent to buildings or natural terrain with extreme vertical gradations that typically reduce GPS accuracy. Trees and buildings create "satellite shadows", limiting the areas where you can reliably collect high-accuracy GPS data. The updated GPS receiver will deliver improved usable data under tree canopy or in natural or urban canyons. Routes that were previously collected accurately will not be recollected in Cycle 6.

TRIMBLE 6000 SERIES GeoXT GPS SPECIFICATIONS		
Receiver	Trimble Maxwell™ 6 GNSS chipset	
Channels	220 channels	
Systems	GPS / GLONASS / WAAS	
Accuracy	Sub-meter	
Operation Temperature	-20 °C to +60 °C (-4 °F to +140 °F)	
Cellular and Wireless	UMTS / HSDPA / GPRS / EDGE / Wi-Fi / Bluetooth	
Internal Still Camera w/ GEOTAG ability	Autofocus 5 MP (JPG) and WMV w/ Audio	

Appendix C Description of Cycle 6 Deliverables

Interim Report Delivery

Partial report will be primarily focused on manually collected routes. The report will be released approximately four months after manual collection of parking lots and other manually collected routes to provide NPS an immediate report on the condition of routes collected manually.

The Interim Report Delivery consists of an Interim Report PDF that contains the following:

- Parking lot and manually rated route conditions
- Route ID Reports
- Route ID Changes Report.

Please note that since the Data Collection Vehicle will have not collected data at this point in time, the following will not be in the Interim Report:

- No park summary information will be provided in the report
- No DCV data will be provided in report
- No road logs will be provided in report
- No maps will be provided in report
- Any mileages collected will be approximate

All data provided in the Interim Report will also be included in the Final Report.

Final Report Delivery

The Final Report will contain all data collected by Manual Inspection and the Data Collection Vehicle. All information provided in the Interim Report will be included in the Final report. Manually collected information reported in the Interim Report may be updated in the Final Report if pavement conditions have substantially changed between the Manual Inspection and Data Collection Vehicle Inspection or other unforeseen circumstances.

The final report will be released approximately 8 months after the Data Collection Vehicle completes its collection of that specific park.

Data included in the Final Report package consists of the following:

- Condition Photos: All photos taken during Cycle 6.
- **Data Video:** Data and video of each route collected by the DCV will viewable through PATHVIEW software. PATHVIEW Software and training will be provided to NPS personnel by Eastern Federal Lands.
- **GPS on All Rated Routes:** All GPS data collected from the DCV will be provided. Parking areas, some roads, and other paved areas that are not fully drivable with the DCV are collected manually by field technicians. GPS is collected for these routes using portable Trimble GPS units.
 - o GPS will be provided as Shapefiles and KMLs
 - o All GPS data related to road collection with be linear referenced to the collected length
- **Geodatabase Background and Metadata:** In addition to this park report, a geodatabase containing both tabular and spatial data specific to this park has been provided.
 - o All data disseminated in the preceding report has been obtained from the tables and fields within said geodatabase. The geodatabase can be referenced for tabular data via Microsoft Access or for both tabular and spatial data via ESRI's ArcGIS Suite of software which consists of; ArcMap, ArcCatalog and ArcExplorer.
 - o Consolidating the RIP data into one database creates a seamless relationship of tables and geographic data. It allows RIP to facilitate easier updates and enhancements in the future. A geodatabase can be thought of as simply a database containing spatial data. A complete and thorough description of the tables and fields contained within this geodatabase can be found in the metadata. The metadata is attached directly within the geodatabase and can be accessed via ESRI's ArcCatalog.
- **Report (RIP Report and Route ID):** A PDF report will be provided that includes a list of all routes and key data. Condition reports for each route will be included. All changes, additions and deletions to any route will be included in the report. Features along routes will not be collected in Cycle 6.

Partial DCV Collections

Additional Partial DCV Collections may be done on specific parks depending on their size and overall mileage of routes within its boundaries during Cycle 6. Parks with greater than 10 miles of paved roadways will receive at least one additional Partial DCV collection during Cycle 6. Data collected during these Partial DCV Collections will not result in the delivery of an additional report to the park.

Data collected by the DCV during Partial DCV Collection will be used to improve HPMA modeling by providing additional "snapshots in time" of park pavement conditions. This improved HMPA modeling will assist in the programing and budgeting of future projects which will help maximize the life of pavement infrastructures.

Instead of receiving a report of conditions collected during the Partial DCV collection, the park will receive a formal letter from the Road Inventory Program requesting coordination for the additional Partial DCV collection, identifying the dates of the Partial DCV Collection and will reinforce the purpose and importance of the Partial DCV Collection.

Appendix D Glossary of Terms and Abbreviations

Glossary of Terms and Abbreviations

TERM OR ABBREVIATION	DESCRIPTION OR DEFINITION
AC	Alligator Cracking
CRS	Condition Rating Sheets (Section 5)
Curb Recommendation	Curb remediation based on overall percentage of curb distress
Curb Reveal	Height of curb exposed from gutter flow line to top of curb
DCV	Data Collection Vehicle
Excellent	Excellent rating with an index value of 95 to 100
Fair	Fair rating with an index value from 61 to 84
FUNCT_CLASS	Functional Classification (see Route ID, Section 2)
Good	Good rating with an index value from 85 to 94
IRI	International Roughness Index
HPMA	Highway Pavement Management Application
Lane Width	Width from road centerline to fogline, or from centerline to edge- of-pavement when no fogline exists
LC	Longitudinal Cracking
MRR	Manually Rated Route
MRL	Manually Rated Line
MRP	Manually Rated Polygon
N/A	Not Applicable
NC	Not Collected
PATCH	Patching and Potholes
Paved Width	Width from edge-of-pavement to edge-of-pavement
PCR	Pavement Condition Rating
PKG	Parking Area
Poor	Poor rating with an index value of 0 to 60
RCI	Roughness Condition Index
SC	Structural Cracking
SCR	Surface Condition Rating
TC	Transverse Cracking